

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
7 February 2002 (07.02.2002)

PCT

(10) International Publication Number
WO 02/010667 A3

(51) International Patent Classification⁷: **F41H 5/04**,
A41D 31/00, B32B 3/16, 33/00, 31/00

MN 55109 (US). **SEONG-GI, Baek, Ph., D.** [KR/US];
1293 Kenilworth Drive, Woodbury, MN 55125 (US).

(21) International Application Number: PCT/US01/21541

(74) Agents: **MALCOLM, D., Reid** et al.; Gray, Plant, Mooty,
Mooty & Bennett, P.A., P.O. Box 2906, Minneapolis, MN
55402-0906 (US).

(22) International Filing Date: 6 July 2001 (06.07.2001)

(25) Filing Language: English

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM,
HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK,
LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX,
MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL,
TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(26) Publication Language: English

(30) Priority Data:
09/610,748 6 July 2000 (06.07.2000) US

(71) Applicant (*for all designated States except US*): **HIGHER
DIMENSION MEDICAL, INC.** [US/US]; 570 Hale Ave-
nue, Oakdale, MN 55128 (US).

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE,
IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF,
CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).


(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **YOUNG-HWA,
Kim, Ph., D.** [US/US]; 353 Lindsay Road, Hudson, WI
54016 (US). **HONG, Ji** [US/US]; 9613 Hillingdon Road,
Woodbury, MN 55125 (US). **RENNEBERG, Nicole,
Dawn** [US/US]; 2434 E. 14th Avenue, #2, North St. Paul,

Published:
— with international search report

[Continued on next page]

(54) Title: SUPPLE PENETRATION RESISTANT FABRIC AND METHOD OF MAKING



(57) Abstract: A puncture, pierce, and cut resistant fabric comprised of a plurality of sheets (14, 18) of plates (12) arranged in a repeating pattern. A material interconnects the plates. The fabric (10) is twistable, bendable, and flexible. It is constructed of substances that will withstand cutting, puncture, and piercing forces encountered in medical or other environments.



WO 02/010667 A3



— *before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments*

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(88) Date of publication of the international search report:

17 October 2002

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 01/21541

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 F41H5/04 A41D31/00 B32B3/16 B32B33/00 B32B31/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 F41H A41D B41F B32B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	DATABASE WPI Week 196800 Derwent Publications Ltd., London, GB; AN 1968-10129q XP002194884 & IT 737 334 A (GRUPPO FINANZIARIO TESSILE SAS DI FL), 1968 abstract	1-83
A	WO 98 53715 A (KIM YOUNG HWA ;HIGHER DIMENSION MEDICAL INC (US)) 3 December 1998 (1998-12-03) claims 1-54; figures 1C,8A,8B,40-43	
Y	DE 29 27 653 A (HOPP ING BUERO) 29 January 1981 (1981-01-29) page 11-12, paragraph 4; claims 1,3,4,6-15; figure 2	1-83
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- * & * document member of the same patent family

Date of the actual completion of the international search

17 July 2002

Date of mailing of the international search report

09/08/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Derz, T

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/US 01/21541

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 028 476 A (SACKS MICHAEL) 13 May 1981 (1981-05-13) claims 1-3,5-7 ----	
A	WO 92 20519 A (ALLIED SIGNAL INC) 26 November 1992 (1992-11-26) the whole document ----	
A	GB 2 238 460 A (PERSONNEL ARMoured DESIGNS LIM) 5 June 1991 (1991-06-05) the whole document ----	
A	GB 2 130 073 A (PERSONNEL ARMoured DESIGNS LIM) 31 May 1984 (1984-05-31) the whole document ----	
A	US 3 894 472 A (DAVIS RICHARD C) 15 July 1975 (1975-07-15) the whole document ----	
A	US 3 867 239 A (GAGNE ROGER A ET AL) 18 February 1975 (1975-02-18) the whole document ----	
A	DE 37 18 453 A (KUFNER TEXTILWERKE GMBH) 15 December 1988 (1988-12-15) claims 1,2,4-6,15; figures 1,2A,2B, ----	
A	DATABASE WPI Derwent Publications Ltd., London, GB; AN 1977-47711y XP002194885 & JP 52 062502 A (NIPPON SYNTHETIC CHEM IND CO), 1977 abstract -----	

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US 01/21541

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☒ Claims Nos.:
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
see FURTHER INFORMATION sheet PCT/ISA/210
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this International application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

Continuation of Box I.2

In view of the large number and also the wording of the claims presently on file, which render it difficult, if not impossible, to determine the matter for which protection is sought, the present application fails to comply with the clarity and conciseness requirements of Article 6 PCT (see also Rule 6.1(a) PCT) to such an extent that a meaningful search is impossible.

The total of 83 claims comprise 35 independent ones, whereof 28 are product claims, and 7 are method claims (comprising claims 80-83 which, despite their wording are considered to be unity with the rest of claims, because the missing technical feature 'fabric' is interpreted into it as an essential feature).

Consequently, an Incomplete Search on the subject-matter covered by all claims has been conducted, and the search has been carried out for those parts only of the application which do appear to be clear (and concise), namely:

the five examples 'SF15', 'SF16' (heat- or UV-cured), 'SF17' and 'SF22' on p. 47-50 of the description are searched:
(opt. curable) polymer (screen- = silk-screen-) printed (polyester a.o.) fabrics which are resistant to mechanical impacts (e.g. puncture-resistant) & flexible, the plates (silk screen printed polymer or metal putty) can be arranged in spaced relationship (e.g. staggered); several fabrics, positions & shapes of plates are possible as illustrated in the figures 9-15 and 18-19.

All other subject-matter which could be interpreted as other 'examples' distributed over the description (p.27: SF11, SF12, SF13; p.34: SF18; p.36: SF25, SF26) is covered by the searched examples SF15, SF16, SF17, SF22 as indicated above.

This is due to the fact that these 'examples' (1) lack information about the employed materials, (2) are thus much too broad (or functional) or (3) even non-existent (SF13).

The applicant's attention is drawn to the fact that claims, or parts of claims, relating to inventions in respect of which no international search report has been established need not be the subject of an international preliminary examination (Rule 66.1(e) PCT). The applicant is advised that the EPO policy when acting as an International Preliminary Examining Authority is normally not to carry out a preliminary examination on matter which has not been searched. This is the case irrespective of whether or not the claims are amended following receipt of the search report or during any Chapter II procedure.

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 01/21541

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
IT 737334	A		NONE	
WO 9853715	A	03-12-1998	US 5906873 A AU 7696698 A BR 9809475 A CN 1257410 T EP 1022962 A1 JP 2000515935 T WO 9853715 A1	25-05-1999 30-12-1998 20-06-2000 21-06-2000 02-08-2000 28-11-2000 03-12-1998
DE 2927653	A	29-01-1981	DE 2927653 A1	29-01-1981
EP 0028476	A	13-05-1981	AT 4938 T DE 3065184 D1 EP 0028476 A1 GB 2061089 A ,B IE 50359 B1 ZA 8006455 A	15-10-1983 10-11-1983 13-05-1981 13-05-1981 02-04-1986 28-10-1981
WO 9220519	A	26-11-1992	US 5316820 A WO 9220519 A1	31-05-1994 26-11-1992
GB 2238460	A	05-06-1991	AU 6628390 A CA 2072965 A1 WO 9106821 A1	31-05-1991 07-05-1991 16-05-1991
GB 2130073	A	31-05-1984	NONE	
US 3894472	A	15-07-1975	DE 2506691 A1	26-08-1976
US 3867239	A	18-02-1975	NONE	
DE 3718453	A	15-12-1988	DE 3718453 A1	15-12-1988
JP 52062502	A	24-05-1977	NONE	

5 **SUPPLE PENETRATION RESISTANT FABRIC
AND METHOD OF MAKING**

FIELD OF THE INVENTION

 The fabric of this invention is primarily useful to afford excellent defense
and protection against penetration forces including cutting, shearing, and slashing
10 forces, even by jagged or serrated instruments applied at excessive force and
impacts of extended duration. The inventive fabric also provides an excellent
level of penetration resistance to sharp puncturing and piercing forces.

 The fabric is comprised of layers, in which at least one of the layers has an
array of plates. The plates in an array maintain a spaced relationship with each
15 other by means of a material substrate.

 The penetration resistant inventive fabric is suitable for fabrication of
garments and protective coverings that are worn to resist cutting, shearing,
slashing, puncturing, and other penetrating forces. Garments of this fabric include
protective apparel, such as gloves, worn in medical, industrial, abrasive, outdoor,
20 and other environments in which penetrating forces are experienced. Examples of
penetration forces resisted by the inventive fabric include cutting by blades or
saws, including high-speed rotating blades; shearing by scissors or blades;
slashing by knives or sharp-edged, abrasive, or serrated objects; and puncturing or
piercing by needles or pins.

25 **BACKGROUND OF THE INVENTION**

 Numerous attempts have been made to fabricate penetration resistant
fabrics with supple, flexible, bendable, twistable, and tactile characteristics. The

cut, shear, slash, puncture, and pierce resistant fabric of this invention accomplishes each of these necessary goals. A further advantage of this invention is that it is readily adaptable for use in conjunction with conventional liquid barriers. An additional advantage of this fabric is that it can be constructed using
5 breathable materials to increase wearer comfort, especially during extended periods of use of protective garments made from the inventive fabric.

An especially effective and highly desirable use for this fabric is for protective gloves, aprons, sleeves, footwear, and other garments. Gloves and garments constructed from the fabric of this invention find use in the medical
10 industry where a high level of tactility is required such as gloves for surgical use. The fabric is also useful for sports people and outdoors people engaged in fishing, hunting, and similar activities. Gloves and garments constructed from the fabric of this invention are useful for protecting the wearer from industrial injuries in factories, on construction sites, in solid waste handling facilities, and in other such
15 hazardous environments.

Due to the rising numbers of wounds from knives and other cutting instruments, there is a strong demand for an effective and user-comfortable protective barrier against these body cutting, shearing, slashing, and piercing weapons. Furthermore, public safety personnel (police officers, fire fighters,
20 paramedics, and first responders) who must physically examine a person, a corpse, clothing, or other objects are in great need of protection from sharp objects, which might possibly be contaminated with a life-threatening infectious organism.

Currently available, breathable protective gloves and body armor are generally of a knit or woven construction. Knit or woven construction provides
25 minimal protection against blade cutting, such as knives. It provides even less

protection against abrasive or serrated instruments, such as serrated knives, saw blades, jagged metal, or glass. And, it provides virtually no protection against puncture or piercing.

Non-porous and, therefore, non-breathing synthetics constitute the
5 construction of some currently available protective gloves and body armor. Such synthetics include aramids, such as Kevlar®, and polyethylenes, such as Spectra®. Such synthetics may be effective at stopping body-piercing projectiles, such as bullets, but are ineffective at resisting wounds from knives or other sharp or jagged edged objects. Such synthetics are also uncomfortable, since they
10 prevent evaporation of perspiration from the wearer's skin.

Another advantage of the fabric of this invention is that it (i) provides dependable resistance to penetration, while (ii) allowing ease of movement due to its characteristic flexibility, bendability, and twistability, and (iii) optionally can be fabricated of breathable materials to allow evaporation of perspiration.
15 Alternately, the fabric can be fabricated of liquid barrier materials.

SUMMARY OF THE INVENTION

The fabric exhibits properties of flexibility, bendability, twistability, and, optional stretchability, by an arrangement of layers, in which at least one layer is an array of plates connected to form a generally two dimensional sheet.

20 The plates are of a tough, hard, and strong substance that is not friable or brittle. The substance type and the thickness of the individual plates will differ according to its application, such as whether the fabric must be cut or penetration resistant and the level and type of force to be resisted.

The fabric is comprised of layers, in which at least one of the layers has an array of plates. The plates in an array maintain a spaced relationship with each other by means of a material substrate.

The material substrate may be a connecting material to which the plates
5 are affixed or attached and it may become an integral part of each of the plates in the array. The connecting material interconnects the plates so that the plates are spaced apart from each other throughout the array. The connecting material also serves the important purpose of distributing any force that impinges upon the fabric or any plate or plates in the fabric among the surrounding plates, thereby
10 taking the entire load of the impinging force off any one plate or group of plates. This property of force distribution enhances the strength of the fabric without requiring more dense plate material, thicker plate material, additional layers of plate arrays, stronger bonding materials, or other strength enhancing properties all of which reduce flexibility, tactility, bendability, twistability, and optional
15 stretchability and increase cost. The connecting material also adds the important property of flexibility of the plate array layer by providing a highly flexible medium between the solid plates. The flexibility is due in a large measure by the fact that the connecting material provides spacing between the plates, which is referred to in this disclosure as the gap. These voids allow bending and hinging
20 between the plates, providing suppleness to the fabric. The connecting material is sometimes referred in this description of the inventive fabric as the continuous portion of a plate layer, while the plates themselves are sometimes referred to as the discontinuous portion of the plate layer.

The material substrate may also be a base material to which the plates are
25 affixed or attached and it may become an integral part of each of the plates in the

array. The base material interconnects the plates so that the plates are spaced apart from each other throughout the array. The base material, like the connecting material (although to a lesser degree than the connecting material), may also distribute any force that impinges upon the fabric or any plate or plates in the fabric among the surrounding plates, thereby taking the entire load of the impinging force off any one plate or group of plates. The base material, like the connecting material (although to a lesser degree than the connecting material), also provides flexibility to the fabric. The base material may also be compressible in a direction perpendicular to the sheet of the base material. This property may be desirable in certain applications such as when using the inventive fabric for cleaning, scrubbing, sanding, or other abrading purposes. In these applications, the plates are able to sink into the soft base material and avoid cracking. In other words, base materials acts like a shock absorber.

The connecting and the base materials may support plates on one or both of their surfaces.

In the fabric of this invention, the base material may be combined with and provide support for one or more layers of plates interconnected with connecting material. Alternatively, a layer of plates with connecting material may support itself only or support one or more additional layers of plates with connecting material. The inventive fabric may comprise one or more base materials layered together with one or more connecting materials. The fabric may be comprised of one or more combinations of base material types and connecting material types, each with an array of plates. These layers may be in various stacked arrangements and each layer may have various plate configurations. The base material or the

connecting material may be a non woven or woven fabric. The base material or connecting material may be breathable or may be a liquid barrier.

A representative method of manufacture of a fabric having a single plate layer array on a single connecting material with a single base material begins by positioning connecting material atop base material. A template of the plate layer array is then positioned atop the connecting material. A suitable substance for formation of the plates is printed onto the connecting material through the plate pattern array of the template and the template is removed. Depending on the substance of the plates, the plates may be subjected to curing or other post-patterning treatments.

If the connecting material is an elastomeric material, the degree of stretch of the fabric must be limited. If the fabric over stretches, the spacing between the plates may increase to such a degree that unwanted penetration is permitted. Several arrangements for limiting stretch are available. A non-stretchable fiber may be affixed to the elastomeric connecting material in such a way that in the fabric's unstretched state the fiber has slack. As the fabric stretches, the slack is taken up. At the end-point, where no more slack exists in the non-stretchable fiber, the fiber prevents further stretch of the elastomer. Other means of limiting over stretching involve judicious use of non-stretchable or stretch limiting connecting material at selected portions of the plate array, with due regard for the final use required for the fabric.

The inventive fabric can be fabricated to be worn on the body. Or, the fabric may be used to cover and protect an article or substrate such as cutting, shearing, or slashing instruments from sustaining damage to their sharp-edged surfaces or from causing damage to persons or their surrounding environment.

The inventive fabric may incorporate differing materials as may be necessary to meet the design, strength, dimensional, and other specifications for various applications. A particular feature of the inventive fabric is that while the plates themselves may be hard the connecting material may be highly flexible, bendable, twistable, and stretchable. In other words, the fabric has the property of being locally hard (that is the plates are hard), while retaining global suppleness across an expanse of the fabric due to the flexibility of the connecting material between the hard plates and the softness and flexibility of the base material. The inventive fabric may even exhibit relative softness and conformance to the body or article over which it is draped. The addition of a suitable liquid barrier layer or treatment of the fabric with a liquid resistant substance resists migration of fluids through the fabric.

Further objectives and advantages of the present invention will become readily apparent to those skilled in this art from the following written description of this specification. To illustrate the invention, the DESCRIPTION OF THE INVENTION section of this specification shows and describes certain embodiments of the invention. However, as will be realized, the inventive fabric is capable of numerous arrangements of its constituent elements to meet the requirements of various uses of the fabric, without departing from the scope of the present invention. For example, the fabric may use one or more layers of plate arrays. The geometry of the plates of the fabric may be identical or differ in any one layer or from layer to layer. Various laminations of plate layer arrays, base materials, and connecting materials may comprise the inventive fabric. Accordingly, the drawings and description of the invention set forth in this specification are only illustrative in nature, and not restrictive.

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is plan view of a fabric embodiment having a stack of layers, a first and lowest layer of guard plates; a second superimposed staggered layer of guard plates on top of the first layer of guard plates; and a third exterior layer of aperture plates on top of the second layer of guard plates, which together cover the entire fabric area.

Figure 2 is a plan view of the fabric of Figure 1 showing only the first and second guard plate layers and the position of bonding spots for bonding the aperture plate layer, but not showing the third exterior layer of aperture plates.

Figure 3 is essentially the same as Figure 1, except that the position of bonding spots for bonding the second guard plate layer to the third guard plate layer is shown.

Figures 4A and 4B are cross-sectional views taken along the lines A and B, respectively, in Figures 1, 2, and 3 showing among other things the position of bonding spots for bonding the layers.

Figure 5 is a plan view of another embodiment of the inventive fabric having first and lowest guard plate layer, second intervening layer of aperture plates, and third layer of guard plates each being staggered and superimposed upon one another, together covering the entire fabric area.

Figure 6 is a plan view of the fabric of Figure 5 showing the first guard plate layer, the aperture plate layer, and the position of bonding spots for bonding the aperture layer to the second guard plate layer.

Figure 7 is a plan view of the fabric of Figure 5 showing the three layers and the position of bonding spots for bonding the second and third layers.

Figures 8A and 8B are cross-sectional views taken along the lines A and B, respectively, in Figures 5, 6, and 7 showing the position of bonding spots for bonding the layers.

Figure 9 is a plan view of another embodiment of the fabric having first
5 and second superimposed staggered layers of guard plates.

Figures 10A and 10B are cross-sectional views of the fabric of Figure 9, taken along the lines A and B, respectively, showing the guard plate layers interposed by a base material.

Figure 11 is a plan view of a further embodiment of the fabric having three
10 identical superimposed guard plate layers.

Figures 12A and 12B are cross-sectional views of the fabric of Figure 11 taken along the lines A and B, respectively.

Figure 13 is a plan view of another embodiment of the fabric showing the first layer having a pattern of non-identical guard plates.

15 Figure 14 is a plan view of the fabric of Figure 13 showing the second layer superimposed on the first layer.

Figures 15A and 15B are cross-sectional views of the fabric of Figure 14 taken along the lines A and B, respectively, showing the layers interposed by a base material.

20 Figure 16 is a plan view of an additional embodiment of the fabric having first and second superimposed staggered layers of guard plates.

Figures 17A and 17B are cross-sectional views of the fabric of Figure 16 taken along the lines A and B, respectively, showing the layers interposed by a base material.

Figure 18 is a plan view of an additional embodiment of the fabric having first and second superimposed staggered layers of guard plates and a third intervening layer of aperture plates.

Figures 19A and 19B are cross-sectional views of the fabric of Figure 18 taken along the lines A and B, respectively, showing the aperture layer positioned between two sheets of base material.

Figure 20 is a plan view of an embodiment of the fabric having first and second superimposed staggered layers of guard plates and a third intervening layer of aperture plates.

Figures 21A and 21B are cross-sectional views of the fabric of Figure 20 taken along the lines A and B, respectively, showing the aperture plates embedded into the base material.

Figure 22 is a plan view of another embodiment of the fabric having first and lowest and third and top superimposed, staggered layers of guard plates and a second intervening layer of aperture plates, together covering the entire fabric surface.

Figure 23 is a plan view of the fabric of Figure 22 showing the first guard plate layer and the aperture plate layer and the position of bonding spots for bonding the second guard plate layer.

Figures 24A, 24B, and 24C are cross-sectional views of the fabric of Figure 22 taken along the lines A, B and C, respectively.

Figure 25 is a plan view of another embodiment of the fabric having first and second superimposed, staggered layers of guard plates and a third and top aperture plate layer, which also shows the position of bonding spots.

Figures 26A and 26B are cross-sectional views of the fabric of Figure 25 taken along the lines A and B, respectively.

Figures 27A, B, and C are cross-sectional views of a further embodiment of the fabric of this invention comprising guard plate arrays having integral metal wire-mesh reinforcement.

Figure 28 is a plan view of another embodiment comprising a first layer of hexagons and a second layer of parallelograms.

Figures 29A and 29B are cross-sections of Figure 28 taken along lines A and B of Figure 28, respectively.

Figure 30 is a cross-sectional view of another embodiment of the fabric of this invention comprising a metal guard plate layer.

Figure 31 shows a cross section of Figure 9 using metal for the guard plates instead of polymer.

Figure 32 illustrates a 21G medical needle impinging upon a metal guard plate fabric embodiment.

Figure 33 is a cross-sectional view of a fabric that is a hybrid of wire-mesh and metal guard plate fabric embodiments.

Figure 34 illustrates another method for bonding multiple layers together.

DESCRIPTION OF THE INVENTION

20 INTRODUCTION

A primary objective of the present invention is to provide a fabric with superior penetration resistance, while at the same time maintaining a high degree of fabric flexibility. Depending on the intended application, the fabric can also be constructed to provide abrasion-resistance, abrasiveness, enhanced grip characteristics, breathability, and other desirable characteristics.

EXPLANATION OF TERMS

To assist with the understanding of the inventive fabric, an explanation of some of the terms used in this disclosure is provided. The explanation of the terms is not intended to be either a definition or an exhaustive explanation of those
5 terms. A full understanding of those terms is to be garnered from the explanations, the entire written description of the invention, the drawings, and the claims set forth in this disclosure in conjunction with the common understanding of those terms by one skilled in the art.

“Aperture” refers to an area of the fabric not covered by any plate when
10 two or more plate layers are superimposed on each other or, in other words, it is an area of overlapping gaps in a fabric having two or more plate layers superimposed on each other.

“Aperture plates” are plates that usually have a smaller area and cover a smaller expanse of the fabric than guard plates. Generally, aperture plates are
15 positioned to cover apertures not covered by superimposed guard plate layers.

“Base material” refers to a sheet-like material that is generally a non-woven fabric. A layer with connecting material may be supported on a base material. The base material provides resistance to fabric tearing and over all strength to the fabric. The base material may be selected for, among other
20 characteristics, flexibility, strength, bonding characteristics with the plate substance, compressibility, liquid impermeability, chemical resistance, breathability, and washability depending on the use of the final product made from the inventive fabric. The base material provides horizontal and optional vertical integration to the fabric. When the plates are established on the base
25 material, whether or not the base material supports a connecting material, the base

material allows the substance of the plates to penetrate into the base material and/or to adhere to the base material. The base material may be, but need not be, penetrated by the plate substance to achieve optimum bonding with the plates.

Examples of suitable materials for base material are nylon, polyester,

5 polyaramide, acrylic, and cellulose material.

“Connecting material” refers to a porous flexible material. It may be a loosely woven fabric or a web of fibers or bands. For certain fabrics of this invention, an array of plates is established on a connecting material. For certain inventive fabrics, the connecting material may be supported on a base material. A
10 representative example of a suitable connecting material is polyester chiffon. The connecting material is selected for its porosity and flexibility. It is also selected for its ability to provide a connection between plates in a layer and for its ability to enhance the resistance of a plate to debonding stresses exerted on the individual plate by spreading the debonding forces throughout the array of plates rather than
15 concentrating the debonding forces on a single plate or a few plates. When the plates are established on the connecting material, whether or not the connecting material is supported on a base material, the connecting material allows the substance of the plates or the bonding of the adhesive for the plates to penetrate through the connecting material.

20 “Fabric” refers to the inventive fabric of this disclosure. It is an arrangement of at least one layer, in which the layer is an ordered array of plates. Each plate array is maintained and stabilized in position by a material. Each plate array may be established on a connecting material, on a base material, or on a connecting material supported on a base material.

25 “Gap” is an area in a plate layer that is not covered by plates.

“Guard plates” are plates that usually have a larger area and cover a larger expanse of the fabric than aperture plates.

“Layer” refers to an array of plates embedded in connecting or base material. In a plate layer, plates are not directly connected to each other. The
5 connecting or base material maintains the positions of the plates relative to each other in an array and maintains the gap between adjacent plates.

“Plate” refers to an individual plate-like object. A plate may have any suitable shape. A plate is generally planar, but need not be. In a penetration resistant inventive fabric, the plates are constructed of a penetration resistant
10 substance. The plates may optionally have other characteristics, such as enhanced grip and abrasion resistance. The term plate refers to both guard plates and aperture plates.

“Registration” refers to superimposing, or stacking, two or more plate layers in proper relative positions to each other so that the penetration resistant
15 fabric provides maximum cut and puncture resistance against needle-like or knife-like objects. Generally, plate layers are superimposed on each other to minimize the size and spacing of apertures of the fabric.

“Substance” refers to the stuff, matter, or constituent component of which the plates are constructed, as exemplified by an element, compound, alloy or
20 composition. The substance may be tough, hard, and strong, and not friable or brittle depending upon the application. The substance type and the thickness of the plates will differ for needle penetration resistance, for cut resistance, and for resistance to other forces depending on the encountered level of force.

PRINCIPLES OF INVENTION

A typical embodiment of the fabric of this invention contains multiple layers of guard plates with the guard plates in each layer connected to a base material or to a base material and an overlay of connecting material. The guard plates are manufactured of a substance selected for its resistance to penetration and optionally for added features of grip enhancement and abrasion resistance. The base material provides overall strength to the fabric, including resistance to tearing and overstretching. It is selected for its flexibility as well as its strength, for its ability to bond with the plate substance, and for other desirable features. Other characteristics may be important for the base material, such as breathability and washability, depending on the use of the final product made from the inventive fabric. The connecting material is selected for its porosity and flexibility. It is also selected for its ability to provide a connection between plates in a layer and for its ability to enhance the strength of the bond between the plate array and the base material.

The composite nature of the inventive fabric makes it possible to realize locally (that is at the plate level) hard, puncture, and cut resistant plate features. At the same time, the fabric may exhibit global (that is overall) softness and flexibility due to the degree of softness and flexibility of the base material and the connecting material chosen for a particular application.

By judicious selection of substances, the fabric of this invention can resist a wide range of sub-ballistic forces. The fabric is not designed to resist ballistic forces due its inherent design. The large size and extremely high speed of a ballistic force dictates that ballistic impact involves a large degree of fiber tensile extension and stress wave energy dissipation over an area much larger than the

size of a bullet. This makes it critically important that ballistic resistance materials must use fibers with high tensile strength, modulus, and energy to break. A similar situation occurs in puncturing of a fabric by a blunt probe. If the tip size of the blunt probe is sufficiently large, the dominant mode of penetration is stretching and breaking of fibers in the fabric. In the process of needle penetration through a fabric, the sharp tip of a needle can penetrate fabric simply by opening up gaps between weaves. A needle penetration process, therefore, does not necessarily involve tensile extension and breaking of fabric fiber. The design philosophy must be fundamentally different.

To provide penetration resistance, one approach is to have a high level of coverage by penetration resistant plates to increase the probability that a needle or other penetrating instrument will encounter puncture resistant plates. The fabric of this invention will provide 100% plate coverage with three layers of plates. The term "plate" refers to both guard plates and aperture plates. Typically, the three plate layers must also be sized and positioned correctly in order to achieve 100% coverage. The fabrics illustrated in Figures 1 – 4, Figures 5 – 8, Figures 11 and 12, Figures 18 and 19, Figures 20 and 21, Figures 22 – 24 and Figures 25 and 26 are all three-layer assemblies. These three-layer assembly fabrics achieve 100% plate coverage in a direction perpendicular to the fabric surface.

Figures 9 and 10, Figures 13 – 15, Figures 16 and 17, Figures 28 and 29, Figures 31 and 32 are two-layer assemblies. Although, plate coverage of the fabric surface with a two-layer assembly is not 100%, the open area fraction of the fabric can be limited to only a few percent. This is done by adjusting the ratio between plate and aperture size, the position of the aperture, and by offsetting the two plate layers to minimize aperture size. For example, in the equilateral

hexagon guard plate array of Figures 9 – 10, the hexagon guard plate minor diameter is 80 mils and the gap between adjacent guard plates is 12 mils. The result is that the open area of the registered two-layer fabric assembly is about 3.4%. Additionally, adjusting the gap size between adjacent plates in a layer can
5 reduce the size of apertures in a two-layer fabric to be smaller than the diameter of a needle probe. Aperture size minimization has the benefit of increased puncture resistance at the aperture-locations. As compared to three-layer assemblies of the inventive fabric, two-layer assemblies cost less to manufacture. Achieving and maintaining the optimal registration is important for two layer fabric assemblies.
10 For example, the aperture-size for hexagon plates tends to fluctuate a significantly for differing registration of layers in an assembled fabric.

Figures 27 shows a method of making a reinforced guard plate layer using wire mesh. Typically, the wire mesh would be metal, but other substances may be used depending upon the application. The fabric of Figure 27 is fabricated using
15 wire-mesh as reinforcement for the polymeric guardplates. The wire mesh is embedded in the guard plate resin before the resin sets. The process includes placing the wire mesh on a connecting material, pouring the guard plate resin over the wire mesh-connecting material combination, placing a photo mask patterned in the form of an array of guard plates over the wire mesh-connecting material
20 combination so that the photo mask pattern has openings in the guard plate locations, curing the guard plate resin with ultra violet light, washing away the uncured resin between the guard plates (in the gaps), and etching away the exposed metal mesh between (in the gaps) the guard plates. The fabric produced by this process has an array of metal wire mesh reinforced guard plates connected

together by connecting material, which extends between the gaps and through the guard plates.

In this disclosure, embodiments of the inventive fabric are sometimes referred to by the designation SF11, SF12, SF13, and so forth for ease of
5 reference.

An octagon-and-square plate array has the benefit of much reduced sensitivity in fluctuation of the aperture-size when the registration of layers is away from its predetermined initial position, which allows for a larger registration tolerance. For example, in the equilateral octagon-and-square guard plate two
10 layer array of Figures 16 and 17 (SF18), the octagon guard plate minor diameter is 80 mils and the gap between adjacent guard plates is 12 mils. The open area of this registered two-layer fabric assembly is about 3.4%, identical to that of the two layer hexagon array of the fabric of Figures 9 and 10 (SF15). However, the size and density of apertures in the multi-layer fabric for SF15 and SF18 are different.
15 The SF18 two layer octagon-and square array has smaller but more numerous apertures than the SF15 two layer hexagon array. For the same guard plate and aperture sizes, the individual aperture size in the SF18 fabric is about 80% smaller and more numerous than the apertures for the SF15 fabric.

A polymer resin is suitable for use as the plate substance for the inventive
20 fabric. In choosing a polymeric resin as a plate substance, it is important to ensure a strong bond between the polymer resin and the base material. A suitable polymer resin for construction of the plates is a one-part heat-curable epoxy resin formulated to (i) provide puncture and cut resistance appropriate to the application of the fabric, (ii) be screen printable, (iii) be flexible and yet strong, (iv) bondable
25 to the base material, and (iii) have good shape definition during printing and

curing. Such resins are readily formulated to meet these criteria and are available from, for example, Fielco Industries, Inc., 1957 Pioneer Rd., Huntingdon Valley, PA 19006, which has formulated a resin that meets the characteristics set forth in this paragraph and has given it the designation: TR21. And TR84. A suitable base
5 material is a non-woven polyurethane and nylon synthetic leather, such as Amara®, available from Clarino America Corp., 489 Fifth Ave., 31st Floor, New York, NY 10017. Other suitable materials include woven or non woven materials, nylon, polyester, polyaramide, acrylic, cellulosic, and similar materials.

The guard plates and the aperture plates are very thin and of a substance
10 chosen to resist a penetration force equivalent to that exerted by a cutting force of the level and type for which the fabric is to be used and for which it is designed.

It has been known that, if polymer resin plates are printed directly onto a base material, they tend to debond easily when the plate is subject to shear or abrasion forces during use. However, it has been unexpectedly discovered
15 according to this invention that, if a layer of connecting material is laid on the base material before establishing the plate layer array, the bonding between the plate layer and the base material is markedly improved. For example, a connecting material is arranged atop a base material. A plate layer array is established by placing a template of the plate layer array atop the connecting
20 material and printing the plate layer array with a suitable polymer resin. The polymer resin completely penetrates through the connecting material and continues to penetrate through a surface portion of the base material. The connecting material thus becomes an integral part of the plate layer array. Due to the interconnection between the individual plates of the array by the connecting
25 material as an integral part of the plates and of the plate layer array, any force

exerted on the fabric surface that would tend to debond an individual plate is dissipated by the connection of the individual plates to each other through the connecting material.

A connecting material may be any porous and flexible material, which
5 may also be characterized as a web. The connecting material may be any such material into which the plate material may be integrally bonded. A suitable connecting material is any typical commercially available polyester chiffon. The connecting material spreads any force, including an abrasive force, applied to the surface of the fabric between neighboring plates. The lateral connection afforded
10 by the connecting material reduces the debonding stress borne by each individual plate. The connecting material is chosen for its ability to provide an interconnection between plates in a layer, and for its ability to enhance the strength of the bond between the plates and the base material. Because the plates are formed onto and through the connecting material, the presence of a connecting
15 material has the added benefit of re-enforcing each plate with a continuous fiber network. When a connecting material is used together with a base material, the fabric demonstrates enhanced puncture and cut resistance.

Fabrics according to the present invention are able to provide needle
puncture resistance, against a needle impinging upon the fabric at an angle of
20 approximately 90° to the fabric surface and at angles substantially less than 90°. The potential for penetration can be greater from a low-angle needle or similar probe. A low-angle needle may have a greater tendency to lift a plate off the fabric surface or to penetrate through an aperture and then below the top fabric layer. Maintaining a minimal gap size between plates, a minimal open area in
25 superimposed layers, and a minimal vertical distance between layers of the fabric

enhances penetration resistance against even low-angle penetration. Figure 32 depicts a needle of the type used for medical applications being stopped by one embodiment of the fabric after only a slight penetration between the metal plates of the fabric.

5 The minimal gap size depends upon the material used for the guard plate and the thickness of the guard plate. Generally, the gap size should not be smaller than the guard plate thickness to maintain flexibility. The thickness of guard plates range from 5-20 mils for polymers and 1-5 mils for metal. The vertical distance between layers should be below a couple of mils to lower the probability
10 of angle penetration while still maintaining adequate adhesive bonding strength between layers.

The various characteristics of the fabric of the invention must be in balance with each other to ensure the desired global flexibility of the fabric.

Another approach to achieving penetration resistance is to use just one
15 layer of penetration resistant plates. This approach has the advantage of potentially greater fabric flexibility and simplicity in manufacturing than the multi-layer approach. The absence of multiple layers of plates leaves a higher percentage of gap space in comparison to the multi-layer approach. However, when the gap size is narrowed sufficiently in relation to the typical probe tip
20 geometry and dimensions, a significant level of penetration resistance may be expected even at the gap locations.

Figure 32 shows an example of a one-layer puncture resistant fabric using metal guard plate. Here a layer of closely spaced metal guardplates is bonded to a substrate through a flexible adhesive. The substrate can be a base material or a
25 combination of a connecting fabric and a base material. The advantage of using

metal as guardplate material is that the plates can be extremely thin while still providing a high level of penetration resistance. For example, upon static loading, a 2-mil thick 304 stainless steel sheet is puncture proof against a 21 gauge medical needle because the needle fails before the metal does. This allows the gaps
5 between guardplates to be as narrow as two mils without sacrificing overall fabric flexibility.

The tip of a 21gauge medical needle is cut at an angle of 26 degrees as is shown in figure 32. This means that for every 2 mils the needle penetrates into a material, the dimension of its cross section widens by 1 mil. If a 21 gauge medical
10 needle hits directly at a 2-mil wide gap (Figure 32), the tip will penetrate 4 mils when it encounters the edges of two metal guardplates. To advance further, the needle needs to either (i) deform or delaminate the metal plates or (ii) stretch the substrate underneath. Otherwise, it will be jammed by the metal guardplates. Deforming metal plates would incur substantial resistance. If the substrate is
15 designed to strongly resist stretching, and a strong adhesive is used to bond metal to the substrate, a high level of penetration resistance can be expected for the one-layer fabric. The substrate provides two functions here: it acts to maintain the overall integrity of the fabric in the lateral dimensions and it provides the cushion in the thickness direction to insure that the needle will encounter significant
20 resistance before it penetrates the entire fabric.

A two-step process of lamination (bonding) and etching is used to make a one-layer fabric with metal guardplates. A metal sheet (e.g. 2-5mil thick stainless steel) is bonded to a flexible substrate (such as chiffon fabric and synthetic leather Amara) with a flexible bonding agent (e.g. polyurethane). Photo resist films are
25 applied on both sides and the metal is etched to leave disconnected guardplates.

The etching technology can control the gap size with precision down to the thickness of the metal sheet. This produces the combination of extremely strong guardplates with very narrow gaps.

One hundred percent plate coverage is not as important for cut resistance as for puncture resistance. For a cut resistance fabric it is important that the plates be made of a cut resistant material. Metal, ceramic, and polymer resins reinforced with mineral or metal particles are examples of good cut-resistant substances for the plates of this inventive cut resistant fabric. A suitable polymer resin is a one-part heat-curable epoxy resin, which can be formulated, to meet the needs of various fabric applications, by Fielco Industries, Inc., 1957 Pioneer Rd., Huntingdon Valley, PA 19006 (as previously stated, designated by Fielco as TR21) or a metal-filled or mineral-filled epoxy putty, such as Devcon Plastic Steel® Putty (A), manufactured by ITW Devcon, 30 Endicott St., Danvers, MA 01923.

It is also important for cut resistance that there are no straight-line areas of the fabric that are uncovered by plates. Therefore, this is a determining factor in the choice of the (i) patterns of the plates, (ii) shape of the plates, (iii) size of the plates, and (iv) size of the gap between the plates. All of these interrelated factors must be controlled in the design of a fabric embodiment to assure that there are no straight lines of exposed, uncovered fabric, that is, no straight lines of fabric that are uncovered by plates. A hexagon pattern, for example, as seen in the guard plate layers of Figure 9, provides a good example where the ratio of plate to gap size is satisfactorily large.

Flexibility is another important attribute for a successful fabric of this invention. In a multi-layer fabric, each plate layer must be flexible. The

flexibility of the base material and connecting material, the plate geometry and size, and the aperture size between plates all contribute to the flexibility of the fabric. A critical control factor to the overall flexibility of the inventive fabric is the integration of layers, that is, the position of the layers superimposed on each other and the position, density, and substance of the bonding agent. The cured bonding agent must remain flexible. In the SF11 (Figures 1 – 4) and SF12 fabrics (Figures 5 – 8), bonding the layers at the spots indicated achieves maximum flexibility for fabrics with the illustrated plate arrays. Note that with the bonding schemes illustrated in Figures 1 – 8, adhesives do not connect plates together in different layers. The adhesives interconnect solely between connecting and/or base material of different layers. This arrangement enhances and maximizes flexibility of the fabric. Typically, a two-layer fabric of this invention is more flexible than a three-layer fabric. The presence of additional layers in the fabric increases the penetration resistance, especially to low angle penetration.

However, the presence of additional layers requires more precise registration between the layers to maintain minimal aperture size between the plates in the multi-layer fabric. Relative motion between layers and plates is decoupled to allow maximize overall flexibility. The decoupling is largely due to the flexibility of the connecting and/or base material. Both of these materials allow stretch of each of the respective layers of the fabric. The bonding limits the stretch of one layer relative to another, but not to a degree that inhibits the desired flexibility of the multi-layered fabric due to the fact that the bonding does not occur between plates in adjacent layers, but between connecting and/or base material.

In fabrics such as SF15 (Figures 9 – 10), SF17 (Figures 13 – 15), and SF22 (Figures 18 – 19), a base material of a certain thickness provides a support for

different plate layers. A connecting material maintains the guard plates of each layer in position relative to each other. The thickness of the relatively soft base material functions as a cushion to limit interference between the motion of plates in the layers separated by the base material, which increases fabric flexibility.

5 The fabric of this invention can also be constructed to provide a liquid barrier. If the fabric uses a base material, the base material itself can be liquid proof or can be treated with any suitable commercially available liquid-proof coating, such as silicone and polyurethane. Alternatively, the fabric itself can be constructed with an additional liquid proof barrier layer, such as latex or
10 polyurethane.

 Depending on the environment within which the fabric of this invention is used, breathability may be another important characteristic of the fabric. A fabric constructed with layers using only connecting material is inherently breathable, because the connecting material in the gaps between the plates is very porous. For
15 fabrics constructed with layers using a base material, the fabric is breathable if the base material is chosen to be breathable.

 The local (hard) and global (supple) properties of the fabric facilitate incorporation of other desirable features into the fabric, in addition to the penetration resistant features described above. For example, polymer resins for
20 the plates can be chosen to maximize static friction between the fabric and wood, steel, fish, glass, or other surfaces. Static friction is particularly important in gloves for industrial uses and outdoor sport uses where grip is an important consideration. Coating the polymer resin plates with a high coefficient of friction material can further increase grip strength. Therefore, gloves can be customized
25 for each specific application by choosing a plate material to suit the frictional

needs of the application. Resins may be readily formulated to meet a variety of high grip strength applications. Fielco readily formulated a resin that provides good grip for stainless steel surfaces. Devcon provides a good resin for galvanized steel surfaces. Another example of a useful product of the fabric of this invention is a flexible cleaning cloth with specialized imprinted plates designed for optimum abrasiveness. For example, a polymer with a metal filler may be used to provide an abrasive surface. An abrasive fabric of this invention may be a single plate layer array established on base material with connecting material overlay. A glove, mop, cloth, pad, or similar item fabricated of such a fabric is suitable for cleaning relatively hard surfaces. Such an abrasive fabric may also serve for wet or dry sanding. Again, the abrasion characteristics of the plates and the flexibility of the base material of the inventive fabric can be separately optimized according to the use characteristics desired in the final product. The suppleness and compressibility of the base material has been found to be of particular importance for design of a fabric used for abrasive purposes. As the abrasive fabric moves across the surface to be abraded, the individual plates are allowed to compress into the base material and thereby conform to the deviations in the abraded surface. Without this compressibility feature, the abrading fabric would not be as efficacious in its ability to smoothly move over the abraded surface and perform function whether it be cleaning or sanding.

DETAILED DESCRIPTION OF THE FABRIC STRUCTURE

The following detailed description of the structure of various embodiments of the penetration resistant fabric of this invention enables any person skilled in the art to make and use this invention and sets forth the best modes contemplated by the inventor for carrying out the invention. Various modifications of the

described embodiments of the inventive fabric, however, will be readily apparent to those skilled in the art because the principles of the present invention are defined in this written description.

In this disclosure, embodiments of the fabric are sometimes referred to by the designation SF11, SF12, SF13, and so forth for ease of reference.

Figures 1 through 4 illustrate a three-layer fabric 10 embodiment, SF11, representing the inventive features of the present invention. As seen in Figures 1 - 3, identical cruciform-shaped guard plates 12 are spaced from each other and oriented in a first guard plate layer 14 with a connecting material 15. All four arms 16 of the cruciform plate 12 are the same. A second guard plate layer 18 is identical to layer 14, also with a connecting material 15. The two layers 14 and 18 are superimposed and oriented to each other to minimize registration of inter-plate spacing 20 between the first and second layers 14 and 18. As seen in Figure 2, in this orientation, the inter-plate spacing 20 forms a non-interconnecting network of generally square-shaped apertures 22 with rounded corners. Figures 4A and 4B are cross-sectional views of the SF11 fabric of Figure 1 - 3, taken along the lines A and B in Figures 1 and 3, respectively, showing the first and second guard plate 12 layers 14 and 18 and the position of bonding spots 27 for bonding the layers 14 and 18 to each other, and the third layer 24 of aperture plates 26 with the position of bonding spots 29 for bonding layer 24 to layer 18. The vertical spacing between layers 14 and 18 shown in Figure 4A differs from that shown in Figure 4B for illustration purposes only. Note that the bonding spots 27 and 29, respectively, are positioned so that they are not directly in a vertical line with each other. This enhances flexibility of the fabric. Furthermore, the bonding spots are at locations where the exposed connecting material of the bonded layers overlap. Bonding is

done at these locations rather than between two rigid plates also to maintain flexibility.

Figure 1 illustrates the superimposed guard plate layers 14, 18, overlaid with a layer 24 of circular aperture plates 26 with a connecting material 15.

5 Figures 4A and 4B are a better illustration of the placement of connecting material 15. The layer 24 is positioned atop the superimposed layers 14 and 18 so that the aperture plates 26 overlay and cover the inter-plate spacing 20 between the first and second layers 14, 18. Figures 2 and 4B illustrate the positioning of bonding spots 29 for attaching the layer 24 of aperture plates 26 to the guard plate 12 layer

10 18. As seen in Figures 1 and 3, the guard plates 12 of layers 14 and 18 and the aperture plates 26 of layer 24 together cover the entire fabric 10. Figure 3 is essentially the same as Figure 1, except that the position of bonding spots 27 for bonding the first guard plate layer to the second guard plate layer is shown.

The SF11 fabric can be manufactured by attaching a chiffon fabric to a

15 metal frame. A stencil with a pattern in the form of an array of plates (such as hexagons) is then placed over the chiffon. The chiffon is backed with a release film and printed with a polymer resin (such as can be formulated by Fielco or Devcon as described in more detail in this specification) through the stencil to form guard plates or aperture plates on the chiffon. The resin usually penetrates

20 through the chiffon to mechanically lock the plates into the chiffon. The printed resin is then cured (by heat, room temperature, moisture, or ultra violet light as may be required by the resin's specification) and the release film is removed to form a plate layer. Multiple layers of plates may be stacked together, depending upon the design parameters required by the application for which the fabric is to

25 be used. To achieve proper registration of the layers to each other so as to

minimize the inter-plate spacing (that is to minimize the number and size of holes extending through the entire stack of layers), the metal frames contain registration holes for properly offsetting layers. This method of manufacture is applicable, with certain variations or additional steps that would be readily apparent to one skilled in the art, for manufacture of other fabric embodiments described in this specification. An example of an alternate for manufacturing a plate layer uses a photo-mask process for forming the plates rather than the stenciling method. In this method a sheet of connecting material is attached to a metal registration frame and the connecting material is then attached on top of a release film. The ultra violet curable resin is then poured on the frame side of the connecting material. Another release film is placed on top of the resin and the resin is spread to form a thin film with the connecting material embedded in it. The film thickness is typically in the 5-10 mil range and can be controlled by the application of pressure on a blade used to spread the resin. A photo mask is then placed on top of the release and the whole assembly is secured together using clips. The resin not blocked by the mask is then cured under an ultra violet lamp. The uncured part of the resin is then washed away using an organic solvent, such as alcohol. After drying, a plate layer is obtained. The photo mask process has the advantage of better resolution control of the gap size between parts, as compared to conventional screen-printing. Using the same photo mask process, the ultra violet curable resin may be pre-mixed with glass fibers. After the washing process, some glass fibers may remain in the gap between the plates. An additional etching step is used to etch away these glass fibers. The plates reinforced with glass are strengthened and more puncture and cut resistant.

Figures 5 – 8 illustrate a fabric embodiment 30, also identified as SF12, of the present invention. The SF12 fabric is comprised of the same layers as in the SF11 fabric 10, but the layers are superimposed upon one another in a different arrangement. As seen in Figure 5, identical cruciform-shaped guard plates 12 are spaced from each other and oriented in a first guard plate layer 14 with a connecting material 15 to maintain the array of guard plates 12. All four arms 16 of the cruciform guard plate 12 are the same. A second guard plate layer 18 is identical to layer 14, also with a connecting material 15 to maintain the guard plate 12 array. The two layers 14 and 18 are superimposed and oriented to each other to minimize registration of inter-plate spacing 20 between the first layer 14 and the third or top layer 18. Interposed between layers 14 and 18 is a second layer 24 of circular aperture plates 26 with a connecting material 15 to maintain the aperture plate 26 array. As seen in Figure 5 and 7, the guard plate arrays 12 of layers 14 and 18 and the aperture plates 26 of layer 24 together cover the entire fabric 30.

Figures 8A and 8B are cross-sectional views of the SF12 fabric of Figures 5 - 7, showing the first and second guard plate layers 14 and 18 and the aperture plate 26 layer 24, with each layer having a connecting material 15 to maintain the guard plate layers 18 and 14 and the aperture plate layer 24. Seen in Figure 8B, are the bonding spots 27 for bonding layers 14 and 24 to each other, and the bonding spots 29 for bonding layers 24 and 18 to each other. Figure 6 also shows the location and patterning of bonding spots 29.

Figures 1 through 8, particularly the cross-sectional views of Figures 4A, 4B, 8A and 8B show the connecting material 15 onto which each of the layers 14, 18, and 24 of plates 12 and 26 are arrayed. The connecting material 15 maintains

the pattern and inter-plate spacing of the plates 12 and 26 of the various layers 14, 18, and 24. The structure and function of the connecting material 15 in relation to the formation of the array of each layer 14, 18, and 24 will be further explained regarding the method of manufacture.

5 Figures 9 and 10 illustrate a fabric 40 embodiment, identified as SF15, embodying novel features of the present invention. As seen in Figure 9, identical equilateral hexagonal-shaped guard plates 42 are spaced from each other and oriented in a first guard plate layer 44 with a connecting material 15. A second layer 46 is also an array of identical equilateral hexagonal-shaped guard plates and
10 is also affixed to connecting material 15. The connecting material 15 maintains the pattern and inter-plate spacings of the plates 42 of each of the layers 44 and 46. The two layers 44 and 46 are superimposed and oriented to each other to minimize registration of inter-plate spacing 48 between the first and third layers 44 and 46. As seen in Figure 9, in this orientation, the inter-plate spacing 48 form
15 a non-interconnecting network of six-pointed star-shaped apertures 50. Interposed between the layers 44 and 46 is a layer of base material 47, with a connecting material 15 overlaying both surfaces 49 of the base material 47. Figures 10A and 10B are cross-sectional views of Figure 9, taken along the lines A and B, respectively. As seen in Figure 9, the guard plates 42 of layers 44 and 46 do not
20 cover the entire fabric 10, but leave uncovered the non-interconnecting network of six-pointed star-shaped apertures 50. The apertures 50 must be sufficiently small to insure optimum guard plate coverage and the layers must be registered to minimize the aperture 50 size.

Manufacture of the SF 15 fabric and other embodiments of fabric of this
25 invention having a base material are made using the process as described in

connection with the SF 11 fabric, except that the base material is first attached to the metal frame and the connecting material is laid on top of the base material. The resin for the plates is stenciled onto the composite of the connecting material and the base material. The resin penetrates the connecting material and attaches to the base material upon curing. The same process can be repeated on the opposite side of the base material to make another opposing plate layer.

Figures 11 and 12 are plan and cross-sectional views, respectively, of another embodiment of the inventive fabric 90, SF16, having three identical superimposed guard plate 42 layers 44, 46, and 92, which are also spot bonded together. As seen in Figure 11, identical equilateral hexagonal-shaped guard plates 42 are spaced from each other and oriented in a first guard plate layer 44 with a connecting material 15. A second guard plate layer 46 is identical to layer 44, also with a connecting material 15. A third guard plate layer 92 is identical to layers 44 and 46, also with a connecting material 15. The connecting material 15 maintains the pattern and inter-plate spacing of the plates 42 of each of the layers 44, 46, and 92. The two layers 44 and 46 are superimposed and oriented to each other to minimize registration of inter-plate spacing 48 between the first and second layers 44 and 46. As seen in Figure 11, in this orientation, the inter-plate spacing 48 form a non-interconnecting network of six-pointed star-shaped apertures 50. The guard plates 42 of the third layer 92, together with the guard plates 42 of layers 44 and 46 provide complete coverage of fabric 90. Figures 12A and 12B are cross-sectional views of fabric 90 of Figure 11, showing the three layers 44, 46, and 92 of guard plates and the three connecting materials 15. Figures 11 and 12 do not show the position of bonding spots in the SF16 fabric. The bonding positions are not commensurate with the guard plate array. That is,

the pattern of bonding spots does not correspond to the patterns of the guard plate arrays. The fabric layers are bonded together to minimize vertical alignment of bonding spots in successive layers of the stack of layers. The incidental occurrence of some bonding spots vertically above each other in the different layers tends to somewhat reduce the fabric flexibility. However, using less overall bonding compensates for this incidental occurrence of vertical alignment of bonding spots throughout multiple layers.

Figures 13 - 15 illustrate a fabric 60 embodiment, identified as SF17, embodying novel features of this invention. As illustrated in Figure 13, the first layer 62 of the fabric is a pattern of guard plates 64 that are equilateral hexagon shapes, with three alternate concave-curved corners. Three adjacent guard plates 64 together form a circular-shaped aperture to provide for a circular-shaped guard plate 66. Note that the overall pattern has an equal number of each guard plates 64 and 66 spaced from each other and oriented in a first guard plate layer 62 with a connecting material 15.

Figure 14 illustrates the second layer 44, identical to the guard plate layer 44, shown in Figure 9, superimposed on the layer 62. Layer 44 has identical equilateral hexagonal-shaped guard plates 42 spaced from each other and oriented in a guard plate layer 44 with a connecting material 15, as seen in the cross-sectional views of Figures 15A and 15B. The two layers 44 and 62 are superimposed and the guard plates 42, 64, and 66 are oriented to each other to minimize registration of inter-plate spacing 68 between the first and second layers 44 and 62. In the orientation shown in Figure 14, the inter-plate spacing 68 form a non-interconnecting network of circularly curved arms. Figures 15A and 15B are cross-sectional views of the SF17 fabric 60 of Figure 14, taken along lines A and

B, respectively. Interposed between the layers 44 and 46 is a base material 47, with a connecting material 15 overlaying both surfaces of the base material 47, as seen in Figures 15A and 15B. As seen in Figure 14, the guard plates 42, 64, and 66 of layers 44 and 62 do not cover the entire fabric 60, because of the non-
5 interconnecting network of curved arm inter-plate spacing 68. It has been determined that it is easier to control the position and minimize the size of apertures in the SF17 style fabric than in the SF15 style fabric. Therefore, the threshold of puncture resistance for SF17 is greater than for SF15.

Figures 16 and 17 illustrate a fabric 120 embodiment, identified as SF18,
10 embodying novel features of the invention. As seen in Figure 16, a layer 122 of an array of equilateral hexagons 124 interposed with an equal number of squares 126 constitute the guard plates 124 and 126. The guard plates 124 and 126 are spaced from each other and oriented in a second guard plate layer 122 with a connecting material 15. A first guard plate layer 128 is identical to layer 122, also
15 with a connecting material 15. The connecting material 15 maintains the pattern and inter-plate spacing of the plates 124 and 126 of each of the layers 122 and 128. The two layers 122 and 128 superimpose and orient to each other to minimize registration of inter-plate spacing 130 between the first and second layers 128 and 122. As seen in Figure 16, the guard plates 124 and 126 of layers
20 122 and 128 do not cover the entire fabric 120. The inter-plate spacing 130 form a non-interconnecting network of square apertures 131. The apertures 131 must be sufficiently small to ensure optimum guard plate coverage of the fabric. Interposed between the layers 122 and 128 is a base material 47, with a connecting material 15 overlaying both surfaces of the base material 47. Figures

17A and 17B are cross-sectional views of Figure 16, taken along the lines A and B, respectively.

Figures 18 and 19 are plan and cross-sectional views, respectively, of another embodiment of the inventive fabric 70, SF22, having first and third
5 superimposed, staggered layers 44 and 46 of guard plates 42 and a second intervening layer 72 of aperture plates 74. As seen in Figure 18, identical equilateral hexagonal-shaped guard plates 42 are spaced from each other and oriented in a first guard plate layer 44 with an interconnection of a connection material 15. A third layer is guard plate layer 46, which is identical to layer 44,
10 also with a connecting material 15. The two guard plate 42 layers 44 are identical to those shown in Figure 9 above. The connecting material 15 maintains the pattern and inter-plate spacing of the plates 42 of each of the layers 44 and 46. The two layers 44 and 46 are superimposed and oriented to each other to minimize registration of inter-plate spacing 48 between the first and third layers 44 and 46.
15 As seen in Figure 9, in this orientation, the inter-plate spacing 48 form a non-interconnecting network of six-pointed star-shaped apertures 50. Figures 19A and 19B are cross-sectional views of the SF22 fabric of Figure 18. Interposed between the layers 44 and 46, as seen in Figures 19A and 19B, are two sheets of base material 47, with a single connecting material 15. The connecting material
20 15 interconnects a second layer 72 of circular aperture plates 74, each of which overlies an aperture 50. As seen in Figure 18, the guard plates 42 of layers 44 and 46 and the aperture plates 74 of layer 72 together cover the entire fabric 70.

Alternatively, a fabric of this inventive embodiment may be assembled without the connecting material for the second layer 72 of circular aperture plates
25 74. The second layer 72 may omit the connecting material 15, because the

aperture plates 74 are not subject to debonding stresses, as they would be if they were surface plates. With or without the connecting material, the second layer 72 of circular aperture plates 74 are established on a first sheet of base material. The second sheet of base material is then pressed onto the layer 72 and the entire
5 assembly is cured to the degree necessary.

Figures 20 - 21 are plan and cross-sectional views, respectively, of a further embodiment of the inventive fabric 80, also designated as SF24, having first and third superimposed, staggered layers 44 and 46 of guard plates 42 and a second intervening layer 72 of aperture plates 74. As seen in Figure 20, identical
10 equilateral hexagonal-shaped guard plates 42 are spaced from each other and oriented in a first guard plate layer 44 with a connecting material 15. The third layer 46, composed of guard plates 42 is identical to layer 44, also with a connecting material 15. The connecting material 15 maintains the pattern and inter-plate spacing of the plates 42 of each of the layers 44 and 46. The two layers
15 44 and 46 are superimposed and oriented to each other to minimize registration of inter-plate spacing 48 between layers 44 and 46. As seen in Figure 9, in this orientation, the inter-plate spacing 48 form a non-interconnecting network of six-pointed star-shaped apertures 50. The first layer and the second layers 44 and 46, both composed of identical guard plates 42 and the second intervening layer 72 of
20 aperture plates 74 are oriented and spaced identically to those shown in Figure 14. Figures 21A and 21B are cross-sectional views of the SF24 fabric of Figure 20. Interposed between the layers 44 and 46 is a base material 47. Figure 21A shows the layer 72 of aperture plates 74 embedded into one surface of the base material 47. The plates 74 are arranged in an array on the base material and then pressed
25 into the base material. Pressing of the plates 74 into the base material may take

place when the plates are uncured, or partly or fully cured. If the plates 74 have not been fully cured before being pressed into the base material, the entire assembly is then cured as required. This embodiment of the fabric with plates embedded into the base material is of reduced flexibility. This technique of
5 embedding plates into base material would not be used for surface plates, particularly where optimum flexibility is required.

A connecting material 15 overlies the surfaces of the base material 47, as seen in Figures 21A and 21B. The guard plates 42 are applied to the base material 47 through the connecting material 15. As seen in Figure 20, the guard plates 42
10 of layers 44 and 46 and the aperture plates 74 of layer 72 together cover the entire fabric 70.

Figures 22 and 23 are plan views and Figures 24A, 24B and 24C are cross-sectional views, respectively, of an embodiment of the inventive fabric 100, SF25, taken along the lines A, B and C, respectively, of Figure 22. Fabric SF25 has first
15 and third superimposed, staggered layers 44 and 46 of guard plates 42 and a second intervening layer 72 of circular aperture plates 74. As seen in Figure 22, identical equilateral hexagonal-shaped guard plates 42 are spaced from each other and oriented in a first guard plate layer 44 with a connecting material 15. A third layer 46 composed of guard plates 42 is identical to layer 44, also with a
20 connecting material 15. The two guard plate 42 layers 44 and 46 are identical to those shown in Figures 9, 11, 17, and 20. The aperture plate 74 layer 72 is identical to those shown in Figures 18 and 20. The connecting material 15 maintains the pattern and inter-plate spacing of the guard plates 42 of each of the layers 44 and 46 and of the aperture plates 74 of the layer 72. The two layers 44
25 and 46 are superimposed and oriented to each other to minimize registration of

inter-plate spacing 48 between the first and second layers 44 and 46. As seen in Figure 9, in this orientation, the inter-plate spacing 48 form a non-interconnecting network of six-pointed star-shaped apertures 50. As illustrated in Figures 22 and 24, the size and positioning of guard plates 42 of layers 44 and 46 and the aperture plates 74 of layer 72 completely cover all of the apertures 50, so that the fabric SF25 is completely covered by the combination of plates 42 and 74. Figure 23 is a view of the layer 72 of aperture plates 74 superimposed on the layer 44 of guard plates 42, and showing the position of bonding spots 102 for bonding the guard plate layer 44 to layer 72. With reference to Figures 24A, 24B and 24C, note that the guard plates 42 of layer 44 and the guard plates 42 of layer 46 are both oriented to the exterior of fabric SF25. Interposed between the layers 44 and 72 are bonding spots 102 and interposed between layers 72 and 46 are bonding spots 104. Between the layers 44 and 46 is the third layer 72 of circular aperture plates 74, each of which overlies an aperture 50.

Figures 25 and 26 are plan and cross-sectional views, respectively, of a further embodiment of the fabric 110 of this invention. This embodiment is also referred to in this disclosure as SF26. Third and second staggered layers 46 and 44 of equilateral hexagonal guard plates 42 superimpose each other, with a third superimposed layer 72 of circular aperture plates 74. As seen in Figure 9, identical equilateral hexagonal-shaped guard plates 42 are spaced from each other and oriented in a second guard plate layer 44 with a connecting material 15. A third guard plate layer 46 is identical to layer 44, also with a connecting material 15. The two guard plate 42 layers 44 are identical to those shown in Figure 9. The connecting material 15 maintains the pattern and inter-plate spacing of the plates 42 of each of the layers 44 and 46. The two layers 44 and 46 are

superimposed and oriented to each other to minimize registration of inter-plate spacing 48 between the third and second layers 46 and 44.

Interposed between the layers 46 and 44 is a base material 47, as seen in the cross-sectional view of Figures 26A and 26B. As seen in Figure 9, in this orientation, the inter-plate spacing 48 form a non-interconnecting network of six-pointed star-shaped apertures 50. The third layer 72 of circular aperture plates 74 overlies one of the layers 44 and 46, with the aperture plates oriented to the exterior of the SF26 fabric. Figure 25 shows a plan view of the bonding spots 112. As seen in Figure 25, the guard plates 42 of layers 46 and 44 and the aperture plates 74 of layer 72 together cover the entire fabric 70.

Figure 28 is a plan view of another embodiment of the fabric 140 of this invention comprising a first layer 144 of hexagons and a second layer 146 of parallelograms 148. Figures 29A and 29B are cross-sections of Figure 28 taken along lines A and B of Figure 28, respectively. As shown in Figures 29A and B, the fabric is also comprised of a base material 47 and connecting material 15 interconnecting the array of hexagons 142 of the first layer 144. The connecting material also interconnects the parallelograms 148 of the second layer 146. The fabric layers 144 and 146 are bonded to the base material 47 in any suitable manner to meet the design needs of the fabric application. The fabric has non-interconnected gaps 143 in the shape of squares.

Figure 27A, B, and C describe a process of making a metal wire reinforced guard plate layer especially suitable for medical material. Puncture resistant material for medical gloves must be soft and flexible to maintain dexterity for medical personnel, yet provide a high level of puncture and cut resistance against sharp medical needles and knives. The softness and flexibility requirement

dictates that the material must be fairly thin, preferably thinner than 1mm. If multiple layers are used, the thickness of each plate layer must be reduced to less than 1mm, which may not be sufficiently strong to resist the puncture and cutting forces encountered in the medical environment. In order to achieve the desired combination of thinness, flexibility, and strength, the polymeric plates must be reinforced or replaced with metal plates. The fabric illustrated in Figures 27A, B, and C utilizes metal wire mesh embedded in the polymer resin used to fabricate the plates. Wire mesh other than metal may also be efficacious, depending upon its type and characteristics. A typical metal wire mesh is less than 10 mils thick and made of steel. Figure 27C illustrates a fabric 50 embodiment of this invention. Figures 27A and 27B illustrate intermediate steps in the manufacture process of the fabric 50.

The fabric of Figure 27C is fabricated with metal wire mesh 52 embedded in the guard plate 54 before the polymeric resin of the guard plate 54 sets. The process includes covering a sheet of connecting material 15 with metal wire mesh 52 and then pouring polymeric resin 53 over the wire mesh-connecting material combination as shown in Figure 27A. Next, a photo mask patterned in the form of an array of guard plates 54 is placed over the wire mesh 52-connecting material 15-resin 53 combination. The photo mask pattern has openings where the guard plate 54 locations are to be in the finished fabric 50. The photo masked material is then exposed to ultra violet light to cure the resin 53 that is not covered by the photo mask, which is the guard plate 54 array. The unexposed, uncured resin 53 in the gaps is then washed away yielding the intermediate fabric illustrated in Figure 27 B. The intermediate fabric now has gaps 55 between guard plates 54. The exposed metal mesh 52 between (in the gaps 55) the guard plates 54 is now

etched away, using ferric chloride for example, to produce the fabric 50 of this invention as shown in Figure 27C. The fabric 50 produced by this process has an array of guard plates 54 integrally reinforced with metal wire mesh 52. And the guard plates 54 are inter-connected by connecting material 15, which extends
5 between the gaps 55 and through and integral with the guard plates 54.

Figures 30A and B are cross-sectional views of another embodiment of this invention comprising a metal guard plate layer 151. The metal guard plate 152 may be, for example, fabricated using 2 to 5-mil thick stainless steel sheet. A metal sheet 155 is bonded to connecting material 15, such as a flexible substrate
10 chiffon, by completely covering the connecting material 15 with a flexible bonding agent 153, such as a polyurethane as shown in Figure 30A. The method of complete coverage results in saturation of the connecting material 15 so that the bonding agent 153 covers both sides of the connecting material 15. Photo resist films are applied to both sides of the composite shown in Figure 30A in a guard
15 plate array pattern and the metal sheet 155 is then etched to leave an array of guard plates 152 that are disconnected from one another as shown in Figure 30B. The photo resist material is removed after the etching step. The guard plate array is held in the pre-defined spatial relationship by the connecting material 15, which is bonded to the guard plates by the flexible bonding agent 153. To further
20 enhance the strength of the fabric 150, a double layer of guard plates 152 can be made by bonding a metal sheet 155 to both sides of the connecting material 15 and then performing the fabrication steps on both sides of the metal bonded connecting material 15 as previously set forth in this paragraph.

An alternative method of bonding the metal sheet 155 to the connecting
25 material 15 by completely covering the connecting material 15 with the bonding

agent 153 as described in the previous paragraph is to spot-bond the connecting material to the metal sheet only at the locations where the guard plates will be positioned in the completed fabric 150. With this method of bonding, a strong, usually rigid epoxy structural adhesive has been effective. No spot bonding
5 adhesive is applied at the gap locations. The bonding agent 153 can be stenciled onto the connecting material 15, after which the metal sheet 155 is bonded to the connecting material 15 before the bonding agent 153 sets. Although, the spot bonding approach results in a fabric 150 that suits certain design criteria, the preferred bonding method is to use a continuous layer of bonding agent 153. The
10 spot bonding method limits the accuracy of the guard plate 152 size and shape and the gap 154 between the guard plates 152 due to the inherent variations in the rheology of the bonding agent adhesives used for spot bonding and the process of screen printing those adhesives. Use of the continuous application of bonding agent is limited only by the etching process, which is very accurate. Using the
15 continuous application of bonding agent 153 allows the creation of narrow gaps, up to the thickness of the metal sheet 155, between the guard plates. This increases the puncture and pierce resistance of the fabric 150.

To maintain proper flexibility of any of the finished fabric embodiments, it is important that the gaps between guard plates are free from materials that may
20 compress or stretch during flexing of the fabric. Because the guard plate material is usually rigid and inflexible, most of the strain caused by bending the fabric is concentrated in the gap region. Even a soft material in the gap region may significantly contribute to the rigidity of the whole fabric because the strain is amplified at the gap region. Jamming of the neighboring guard plates as the fabric
25 is flexed if the gap is too narrow can also compromise flexibility of the fabric.

This jamming of neighboring guard plates occurs when the gap size becomes smaller than the thickness of the guard plate. But with the metal plate in the thickness range of 2-5mils, it is possible to narrow the gap size between the guard plates to as small as the guard plate thickness without compromising overall flexibility. The narrowing of the gap is a worthwhile goal because the smaller the gap the less chance that a penetrating instrument will penetrate the fabric of this invention. Etching technology is sufficiently precise that a gap as thin as a metal sheet thickness in the range of 2-5 mils can be fabricated. A 2-5 mil gap size is much smaller than the typical medical needles, which range from 13 mils for insulin needles to 31 mils for a 21 gauge needle 156, which is shown in Figure 32. A gap between plates of 2 mils will stop a 21 gauge needle from penetrating through the gap into the wearer's skin. And, since flexibility of the fabric is enhanced when the plate thickness is no greater than the gap size, the plate thickness should be no greater than 2 mils. A gap size greater than 5 mils will not stop the penetration of a 21 gauge needle through the fabric and since plate thickness should be no greater than the gap size, the plate thicknesses for use with a 5 mil gap size should be no greater than 5 mils. To reduce the gap to a size that will stop a 21 gauge needle, therefore, requires a plate thickness in the range of 2-5 mils. Typically, polymeric plates are not strong enough to resist penetration of the plate at thicknesses of 5 mils or less. On the other hand, metal plates in the 2-5 mil thickness range are strong enough to resist penetration.

A 21gauge medical needle, as illustrated in Figure 32, consists of a sharp tip followed by a cutting edge. The angle of the tip is about 26 degrees, so that for every 1 mil of gap size between the metal guard plates, the tip of the needle can advance 2 mils. If the gap size between metal guard plates is 2 mils, then as long

as the fabric is thicker than 4 mils, the needle tip will have to break the guard plates around the gap in order to penetrate through the fabric. Even when the needle tip directly hits the gap, it will take a certain level of force for the needle to penetrate through the gap because this involves bending and deforming the metal guard plates, delamination of the adhesive, and tensile stretching of the base material. By optimizing the design parameters when designing the fabric for various applications a sizable resistance may be obtained even at the weakest points of the fabric, the gap between the guard plates. If the gap size between the guard plates is sufficiently small such that the puncture resistance of the gap is adequate, sliding of the needle tip on the surface of the metal plate is less of an issue. In such a case solid metal sheet without any treatment for resisting needle slide can be used and still maintain a high level of puncture resistance.

A material suitable for the metal plates is stainless steel sheet 2 having a 2 to 5 mil thickness. H.B. Fuller UR-2139 and Ciba 2040 polyurethane adhesives have been found to be effective. These adhesives are chosen for their flexibility, their bonding strength, and their ability to maintain good bonding strength after the etching process. An example of the base fabric used with the metal plate construction, with or without wire mesh reinforcement, is Amara. A suitable connecting material for embedding in adhesive is chiffon fabric.

An SF15 fabric, as illustrated in Figures 9 and 10, can be made using the metallized guard plate approach of Figures 30A and B. Two metal guard plate 152 layers are used. Each guard plate 152 layer is offset from the other as described in connection with the SF15 fabric. Between each metal guard plate 152 layer is a base material 47 as illustrated in Figure 31. The base material 47 can be the synthetic leather material Amara. The metal sheet 155 may be bonded

to the base material using a bonding agent 153. Another embodiment of a double metal plate fabric comprises two metal sheets bonded together with or without a connecting or base material between them. A flexible bonding material is most efficacious, but if a rigid bonding material is used, spot bonding rather than

5 continuous bonding of the two sheets is necessary to obtain a flexible fabric. In the two metal sheet embodiment, photoresist films are applied on both sides and the metal is etched to leave disconnected plates to form a flexible plate layer.

Figures 33A and B depict an embodiment of the fabric of this invention comprising metal guard plates reinforced with wire mesh. Figure 33A is an

10 intermediate step in the process of manufacturing the metal guard plate reinforced wire mesh fabric 160. The intermediate step comprises a composite of a metal sheet 155 bonded by a bonding agent 153, such as a flexible adhesive, to connecting material 15, such as chiffon, which is in turn bonded by a suitable bonding agent 153 to a wire mesh 52 with the bonding agent 153 shown on the

15 bottom of the wire mesh 52, which results due to the fact that when the bonding agent 153 is poured on the porous wire mesh 52, it runs through the wire mesh 52. During the fabrication process, as previously described with reference to Figures 27 and 30, the fabric 160 of Figure 33B is formed, which is comprised of metal guard plates 152 reinforced with wire mesh 52 and interconnected with

20 connecting material 15 that is an integral part of a guard plate layer 162. If necessary for a particular application, multiple layers of guard plate layers 162 may be stacked upon one another and may be registered with respect to one another so that the apertures extending through the multiple layer fabric may be minimized in number and size or may be totally eliminated.

Figure 34 illustrates another method for bonding multiple layers together. This method of bonding may be used with almost any embodiment of the fabric depending upon the specific objectives of the particular fabric's use. The objective for this bonding method or arrangement is the same as for other bonding methods illustrated in this disclosure, that is, to bond the layers together securely while not sacrificing the overall flexibility of a multi-layered fabric. The bonding method 80 of Figure 34 achieves this objective by using flexible adhesive arranged in an array of shapes in the form of disconnected lines (or elongated rectangle or similar shapes) 81 with neighboring disconnected line shapes perpendicular to each other.

DESCRIPTION OF FABRIC TESTS

Test Equipment and Procedures

Needle puncture testing was performed on samples of fabric described in this specification using an Imada puncture resistance tester, model number DPS-44R, available from Imada, Inc., 450 Skokie Blvd., Suite 503, Northbrook, IL 60062. The puncture tester is capable of measuring forces in the range of 0-44 pounds. A fabric sample is placed on top of the tester's metal base. A needle (typically 20 mils in diameter with a cone shaped tip) is attached to the tester probe, which is positioned vertically above the fabric sample. The probe moves toward the fabric sample with a fixed velocity (for example, 80 mm/minute). The puncture tester measures and records the peak force attained during the puncture attempt. Each test uses a fresh probe. The standard test is at a 90° angle to the surface of the fabric sample. The tester is adjustable to vary the angle at which the test needle impinges upon the fabric sample.

A cut resistant tester was designed and constructed to test the cut resistance of the fabric claimed in this specification. The cut resistance tester is similar to the standard cut resistance tester described by ASTM F 1790-97, Standard Test Method for Measuring Cut Resistance of Materials Used in Protective Clothing. A fabric sample is mounted on a brass sheet covered wooden drum of the tester. A razor blade, attached to a lever arm of the cut tester, rests against the fabric surface. A predetermined weight is applied to the lever, creating a known cutting force. The drum is hand rotated at a slow, fixed speed so the razor blade cuts against the fabric and parallel to it for a distance of 4 inches. If the razor blade cuts through the sample within the 4 inches, the threshold cut-through force is measured and recorded. If the sample is not cut through within the 4 inches, the test result is recorded as "no-cut." A new razor blade is used for each test.

Test Results of Fabric Samples Using The Puncture and Cut Testers

SF15 Fabric

The SF15 fabric is illustrated and described above with reference to Figures 9 and 10. Amara®, a non-woven polyurethane and nylon synthetic leather, is used as the base material in preparing a sample of SF15. The Amara® base material is about 20 mils (that is, 20 thousands of an inch) thick. A polyester chiffon connecting material is laid on top of the Amara® and polymer resin plates are screen printed onto the materials using a 10 mil thick stainless steel stencil. The printed pattern is a hexagon array with 80 mil hexagons (minor diameter). The gap size between the hexagons is 14 mils. The polymer resin is a one-part heat-curable epoxy resin, formulated by Fielco Industries, Inc., 1957 Pioneer Rd., Huntingdon Valley, PA 19006 and designated as TR21, as previously stated in

this specification. The resin is heat cured at 120° C for one hour. Then, similar stencil printing is done on the other Amara® surface, with the hexagon array properly registered as shown in Figure 10B to obtain the SF15 fabric seen in Figure 9. The resulting SF15 fabric is flexible and is about 45 mils thick.

- 5 Using a grabbit needle as a probe, the puncture resistance of the SF15 sample fabric was determined to be 3.5 ± 0.7 lbs. for a needle impinging the fabric at a 90° angle of attack and 3.1 ± 0.7 lbs. for a 30° angle of attack. The cut resistance measured to be above 7 lbs. A grabbit needle or pin is a pin found in an office supply store. It is about 20 mils in diameter with a cone shaped tip. It is
10 used as a puncture probe because of its sharpness and thinness.

SF16 Fabric

- The SF16 fabric is illustrated and described in this specification with reference to Figures 11 and 12. Devcon Plastic Steel® Putty (A) is screen-printed on polyester chiffon fabric supported on a release backing using a 10-mil thick
15 stainless steel stencil to obtain a guard plate layer as in Figure 11. The resin is heat cured at 70° C for 45 minutes, followed by 4 hours post curing at room temperature. Three identical layers are bonded together in properly registered positions, as shown in Figures 12A and 12B, using FleshTex® polyurethane resin available from Zeller International, 623 Ellen Dr., Winter Park, FL 32789.
20 FleshTex® is a polyurethane-type multi-part (2 or 3 parts) thermoset resin. FleshTex® cures at 70° C for 30 minutes. The total thickness of the SF16 fabric sample was about 65 mils.

- The SF16 sample was puncture tested using a grabbit pin. Under a 2.0-lb. force, no penetration was observed at 90°, 52°, and 30° angles of attack. The cut
25 resistance of the sample was 14 lbs.

SF17 Fabric

The SF17 fabric is illustrated and described in this specification with reference to Figures 13 - 15. Amara®, with a 20-mil thickness, is the base fabric.

The materials used and the printing process is as described above in the section of this specification titled SF15 Fabric. However, the printing of the layer 62 uses a stencil pattern to imprint the SF17 guard plates 64 and 66, as shown in Figure 13. The resulting SF17 fabric is flexible and has a thickness of about 45 mils.

Using a grabbit needle as a probe, the puncture resistance of this SF17 fabric sample measures to be 3.4 ± 0.7 lbs. for a 90° angle of attack, and 3.1 ± 0.7 lbs. for a 30° angle of attack. The cut resistance measures to be 8 lbs.

SF22 Fabric

The SF22 fabric is illustrated with reference to Figures 18 and 19.

Amara®, with a 10-mil thickness, is used as the base material 47. Polyester chiffon, used as the connecting material 15, is laid on top of the Amara® and stenciled with the Fielco polymer resin, as described above in the section titled SF 15, to form the guard plate 42 array layer 44 seen in Figure 19B. The polymer resin is cured as described in the section titled SF15. Two such guard plate 42 array layers 44 and 46 are formed. On layer 44, a layer 72 of circular aperture plates 74 is printed, as illustrated in Figure 19. The layer 72 may be printed through a chiffon layer 15, as in Figures 19A and 19B, although it is also possible to print layer 72 without a chiffon layer. For optimum performance, the aperture layer 72 should incorporate a connecting material 15.

The layers 44, 46, and 72 are bonded together, in properly registered positions, as shown in Figure 19. The guard plate 74 array of layer 72 may or may not be cured before bonding the layers 44, 46, and 72 together. If layer 72

has not been cured before bonding layers 44, 46, and 72, the SF22 fabric 70 is then cured. The resulting SF22 fabric is flexible and has a thickness of about 50 mils.

The puncture resistance for this fabric, using a grabbit pin as the probe, measured to be 3.5 ± 0.5 pounds for a 90° angle of attack and 3.0 ± 0.5 pounds for a 30° angle of attack. The cut resistance measured to be 9 pounds.

SF16 Fabric

Guard plate layers of the wire mesh reinforced fabric are made using the process described in Figure 27. The UV-resin is Ebecryl 645 from UCB Chemicals. The photo-initiator is Irgacure 184 from Ciba. 100 parts of UV resin is mixed with 2 parts of photo-initiator. Wire mesh is from Sefar America, Inc. The wire is made of stainless steel 316 with mesh count of 165x165 per inch. The wire diameter is 0.0025 inch. The opening size is 0.0036 in. The weight density is 6.75 lb/sq. ft.

15

In the SF16 design as shown in Figure 11 and 12, the guard plates are 60-mil hexagons. The gap size is 7 mils. The total thickness of individual layer is 10~12 mils.

For bonding, 31 mil diameter adhesive dots are used. They are separated periodically by 0.34 inch. The bonding adhesive is Fleshtex from Zeller International. 10 parts of FleshTex component A and 10 parts of FleshTex component B are mixed and then added to 0.8 parts of Cab-O-Sil flow modifier.

The samples are tested using a 21 gauge medical needles with a 30 degree angle of attack. This represents one of the harshest conditions for the puncture test. Four samples were made and 20 puncture tests were done on each sample.

The lowest threshold force observed for needle penetration was found to be 1.1 pounds. The average force was 2.26 pounds (the average was based upon 100 data points). The puncture resistance force ranged from 1.1 to 4.0 pounds.

SUMMARY OF DETAILED DESCRIPTION

5 The fabric embodiments of this invention have application for protective garments for individuals working in occupations exposed to potentially injurious penetration, such as public safety officers, machinists, butchers, surgeons, and the like. Depending upon the thickness of the fabric, dimensions and styles of the plates, and the substances and materials from which the fabric of this invention is
10 constructed, the protective garments may have properties ranging from resistance to stabbing and cutting, up to resistance to needles. When the fabric of this invention is used for penetration and puncture resistance, the plates are made of a hard penetration or puncture resistant substance. Preferably, the penetration and puncture resistant apparel or item made from the fabric of this invention will have
15 the hard plates of the array oriented toward the expected source of penetration or puncture. Sport and outdoor apparel of fabric according to this invention may be insect and snake bite proof. Apparel from the present inventive fabric may be suitable for specific activities and environments calling for protection from penetration or puncture, including apparel for riding open uncovered vehicles such
20 as motorcycles, industrial safety apparel, underwater diving wear, and penetration or puncture resistant footwear and head coverings. Other items that require resistance to penetration are made from fabric of this invention, including liquid-retention liners for oil tankers, ponds, landfills, swimming pools and tires. Articles requiring penetration-resistance, including inflatable rafts, light
25 watercraft, such as canoes, kayaks and racing shells, or air mattresses may be

fabricated from fabric of this invention. Apparel for other occupations as well as for applications in the medical and dental fields will require differing penetration and puncture resistant substances and material types. Differing thickness and dimensions of the plates are required, since the forces that come to bear upon the fabric will vary.

For medical gloves, the sizes and shapes of the guard plates and the aperture plates and the substance of which they are made, may vary, according to the particular procedures to be performed and differing conditions. It may not be necessary to fortify an entire glove with a puncture resistant fabric of this invention. The fabric may strategically reinforce only high-risk zones.

This fabric is not dependent upon specific shapes or dimensions of the plates. The fabric is scaleable to meet widely varying possible uses. The choice of shapes and dimensions, and the substance and material of which they are manufactured, are dependent upon the application and are determinable by routine engineering calculations. The fabric of the invention, when manufactured of substances and materials of suitable strength, resistance, and dimensions forms a flexible, cut, puncture, and pierce resistant enclosure for biohazardous and potentially flammable and/or explosive liquids, including gasoline and other petroleum or fuel products. Such flexible enclosures find use as liners in various types of tanks or similar liquid reservoirs.

The substances of which the plates are manufactured are currently available as off-the-shelf goods or in the case of resin are readily formulated by resin manufacturers to meet design parameters required of the fabric for use in various applications. The substances can be, for example, metal (such as stainless steel or titanium), metal alloys, ceramic, polymers, high strength composites (such

as carbon fiber or glass composites), or glass. Any other substance may be used that resists the specified puncture, piercing, and cutting forces at the chosen thickness necessary to achieve the characteristics desired for the application. Other examples of suitable products include epoxy or acrylate resins, such as

5 Darocur®, Epon®, or Ebecryl®; other thermoset resins whether; and mixtures of such resins with other polymers and optionally with various suitable curing agents. Any substance should preferably not be friable or brittle. When the fabric forms a liquid enclosure or receptacle or is used in a liquid environment, the selected substances and materials for the fabric should be resistant to chemical or

10 physical action of the contained liquid.

The process of assembling the fabric of this invention uses currently available production technology and the novel method of printing plates onto a base material, as described in this specification.

The surfaces of any of the plates described in this disclosure may be

15 planar, concave, convex, or any combination thereof, or a specially constructed surface to meet the needs of a particular application. The guard and aperture plates used in the inventive fabric for differing applications will have a thickness sufficient to resist the piercing or cutting force that the fabric is intended to resist. The plates of different layers of the same inventive fabric may each be made of

20 different substances.

A connecting material is any material, which when interconnected between the plates of the fabric, maintains a predetermined spatial relationship of the plates within the fabric and within a prescribed range of motion of the plates relative to one another. To do so, the connecting material should be flexible. The

25 connecting material may be continuous or have certain selected discontinuities, as

long as it performs the needed function of maintaining and connecting the array of plates in the fabric. Any discontinuities in the material may be chosen to enhance the properties of flexibility, bendability, and twistability, and, optionally, stretchability in the fabric or in the useful article made with the fabric. Any

5 discontinuities in the material must be so chosen and located that they do not compromise the required penetration resistance of the fabric either locally or globally or of the useful article constructed of the fabric. Such discontinuities must also be so chosen and located that they do not deleteriously affect the structurally integrity of the fabric or allow any portion of the array to separate.

10 The material may be elastomeric or non-elastomeric. The material is chosen with regard to promoting the desired three degrees of freedom of movement of the fabric of this invention, including flexibility, bendability, and twistability. The material may also be chosen to enhance the desired properties of elasticity and stretchability in the inventive fabric. A stretchable material, such as an elastomer,

15 is an example of a flexible material suitable for performing this function. However, a non-stretchable material is suitable for certain applications. The material may be man-made, naturally existing, or blends of the two.

As with other embodiments set forth in this specification, other variations are appropriate to meet the functional and utilitarian needs of the application.

20 Such variants are choices that come within the spirit and scope of this invention.

This specification has described and illustrated various embodiments of the penetration resistant fabric of the invention. Various arrangements of plates and layers have been described. However, these illustrated and described arrangements are not intended to be the only arrangements for implementing and

25 achieving the objectives of the present invention, nor are they the only possible

embodiments encompassed by this invention. This invention is capable of modification within the scope of the inventive penetration resistant fabric and, therefore, the invention is not limited to the precise details set forth in this specification. This invention includes all changes and alterations that fall within

5 the purview of the appended claims.

What is claimed is:

1. A fabric comprising connecting material and an array of plates affixed to the connecting material, which plates are affixed in a spaced relationship to each other.
2. A fabric comprising connecting material and a plate affixed to connecting material.
3. A fabric comprising connecting material and a plurality of plates affixed to the connecting material, which plates are affixed in a spaced relationship to each other.
4. A fabric comprising connecting material and a plurality of plates affixed to the connecting material, wherein the plates are maintained in a spaced relationship to one another by the connecting material.
5. A fabric comprising a plurality of plates affixed to a means for flexibly connecting the plates together in a spaced relationship.
6. The fabric of any of claims 1 through 5 further comprising more than one layer of fabric in a stack.
7. The fabric of claim 6, wherein the layers in the stack are affixed each other.
8. The fabric of claim 7, wherein the layers in the stack are affixed by bonding them together at locations on the continuous portions of the layers.
9. The fabric of claim 7, wherein the layers in the stack are affixed by bonding them together at locations on the discontinuous portions of the layers.
10. The fabric of claim 7, comprising more than two layers of fabric wherein the affixing locations between each set of adjacent layers is staggered from the affixing locations between each successive set of adjacent layers in the

fabric stack so that the affixing locations between successive adjacent layers are not superimposed.

11. The fabric of claim 7, wherein the layers are affixed together at locations on continuous and discontinuous portions of the layers.
12. The fabric of claim 1, wherein the connecting material is selected from material that is woven, non-woven, porous, flexible and that has a limit to its stretchability.
13. The fabric of claim 1, wherein the plates have an abrasive surface.
14. A fabric comprising base material and an array of plates affixed to at least one side of the base material, which plates are affixed in a spaced relationship to each other.
15. A fabric comprising base material and a plurality of plates affixed to a least one side of the base material.
16. A fabric comprising base material and a plurality of plates affixed to at least one side of the base material, wherein the array of plates are maintained in a spaced relationship to one another by the base material.
17. The fabric of any of claims 14 through 16, further comprising more than one layer of those fabrics in a stack.
18. The fabric of claim 17, wherein the layers in the stack are affixed to each other.
19. The fabric of claim 18, wherein the layers in the stack are affixed to each other by bonding at locations on the base material portions of the layers.
20. The fabric of claim 17, comprising more than two layers of fabric wherein the affixing locations between a first set of adjacent layers is staggered from the affixing locations between successive adjacent layers in the fabric stack so that the affixing locations between successive adjacent layers are not superimposed.

21. The fabric of claim 18, wherein the layers in the stack are affixed together by bonding at a location on at least one of the plates affixed to at least one side of the base material.
22. A fabric of any of claims 14 through 16, comprising plates made of a polymeric substance.
23. A fabric of claim 1, wherein the plates are affixed to the connecting material by bonding.
24. A fabric of claim 1, wherein the plates are affixed to the connecting material by forming an uncured polymeric substance in the form of a plate on the connecting material and then curing the polymeric substance to form the plate, which extends through the connecting material web so that at the location of the plate the connecting material becomes an integral part of the plate.
25. A fabric comprising connecting material, an array of plates affixed to the connecting material, and a mesh reinforcement of the plates, which plates are maintained in a spaced relationship to one another by the connecting material.
26. A fabric comprising base material, an array of plates affixed to the base material, and a mesh reinforcement of the plates, which plates are maintained in a spaced relationship to one another by the base material.
27. The fabric of claim 25 or 26, further comprising more than one layer of the fabric in a stack..
28. A method of making the fabric of claim 25, comprising the steps of:
 - a. covering connecting material with mesh reinforcement;
 - b. coating the connecting material-mesh reinforcement combination with polymeric resin;

- c. placing a photo mask patterned with openings in the form of an array of plates over the connecting material-mesh reinforcement-polymeric resin combination;
 - d. exposing the photo masked combination of step (c) to a curing agent to cure the polymeric resin not covered by the photo mask;
 - e. washing away the unexposed, uncured polymeric resin to form the gaps in the fabric; and
 - f. etching away the exposed mesh reinforcement in the gaps, wherein the fabric has an array of reinforced plates held in a spaced array by connecting material.
29. A method of making the fabric of claims 26, comprising the steps of:
- a. covering base material with mesh reinforcement;
 - b. coating the base material-mesh reinforcement combination with polymeric resin;
 - c. placing a photo mask patterned with openings in the form of an array of plates over the base material-mesh reinforcement-polymeric resin combination;
 - d. exposing the photo masked combination of step (c) to ultra violet light to cure the polymeric resin not covered by the photo mask; and
 - e. washing away the unexposed, uncured polymeric resin to form the gaps in the fabric, wherein the fabric has an array of reinforced plates held in a spaced array by base material and mesh reinforcement.
30. The fabric of claim 27, wherein the mesh reinforcement is metal.

31. A fabric comprising base material affixed to a connecting material, which connecting material has an array of mesh reinforced plates affixed to the connecting material so that the plates are maintained in a spaced relationship to one another.
32. The fabric of claims 25, 26 or 31, comprising plates made of a polymeric substance.
33. A fabric comprising connecting material and an array of metal plates affixed to the connecting material, which plates are maintained in a spaced relationship to one another by the connecting material.
34. A method of making the fabric of claim 33 comprising the steps of:
 - a. coating connecting material with a bonding agent;
 - b. covering the bonding agent coated connecting material with a metal sheet;
 - c. coating the combination of step (b) with a photo resist film patterned with openings in the photo resist film in the form of gaps between an array of plates;
 - d. exposing the photo resist film combination of step (c) to a metal etching material to etch away the metal sheet not covered by the photo resist film; and
 - e. removing the photo resist film, wherein the fabric has an array of metal plates held in a spaced array by connecting material.
35. A method of making the fabric of claim 33, comprising the steps of:
 - a. applying bonding material to connecting material at those areas where plates will be located on the connecting material;
 - b. covering the bonding agent coated connecting material with a metal sheet;

- c. coating the combination of step (b) with a photo resist film patterned with openings in the photo resist film in the form of gaps between an array of plates;
 - d. exposing the photo resist film combination of step (c) to a metal etching material to etch away the metal sheet not covered by the photo resist film; and
 - e. removing the photo resist film, wherein the fabric has an array of metal plates held in a spaced array by connecting material.
- 36. The fabric of claims 1, 14, 27 or 33, wherein the thickness of the plate is not greater than size of the gap between the plates.
- 37. The fabric of claim 36, wherein the plate material thickness is in the range of 2-5 mils.
- 38. A fabric comprising:
 - a. a base material;
 - b. a first connecting material bonded on a first surface of the base material and a second connecting material bonded on a second surface of the base material, each of the first and second connecting material having an array of metal plates affixed to the first and second connecting material so that the first and second connecting material maintain the plates in pre-spaced relationship to one another; and
 - c. each of the first and second connecting material having its array of metal plates oriented to each other to minimize registration of inter-plate apertures between the plates.
- 39. A fabric comprising:
 - a. a first connecting material and an array of metal plates affixed to the first connecting material, which plates are maintained

in a spaced relationship to one another by the first connecting material;

b. a second connecting material and an array of metal plates affixed to the second connecting material, which plates are maintained in a spaced relationship to one another by the second connecting material; and

c. the second connecting material affixed to the first connecting material in an orientation to each other to minimize registration of inter-plate apertures between the plates.

40. A fabric comprising a first array of metal plates bonded to a second array of metal plates so that each layer of metal plates is held in a spaced array by the other layer of metal plates, the first array of metal plates oriented to the second array of metal plates to minimize registration of inter-plate apertures between the plates

41. A method of making a fabric, comprising the steps of:

a. applying bonding material to a first metal sheet;

b. covering the bonding material with a second metal sheet;

c. coating the first metal sheet of the combination of step (b) with a first photo resist film patterned with openings in the first photo resist film in the form of gaps between an array of plates;

d. coating the second metal sheet of the combination of step (b) with a second photo resist film patterned with openings in the second photo resist film in the form of gaps between an array of plates, the second photo resist film oriented to the first photo resist film to minimize registration of inter-plate apertures between the plates;

- e. exposing the first and second photo resist film combination of step (d) to a metal etching material to etch away the metal sheet not covered by the photo resist film; and
- f. removing the photo resist film, wherein the fabric has a first and second layer of metal plates, each layer of metal plates held in a spaced array by the other layer of metal plates.

42. A method of making a fabric, comprising the steps of:

- a. applying bonding spots to a first metal sheet;
- b. covering the first metal sheet of step (a) to a second metal sheet;
- c. coating the first metal sheet of step (b) with a first photo resist film patterned with openings in the first photo resist film in the form of gaps between an array of plates;
- d. coating the second metal sheet of step (b) with a second photo resist film patterned with openings in the second photo resist film in the form of gaps between an array of plates, the second photo resist film oriented to the first photo resist film to minimize registration of inter-plate apertures between the plates;
- e. exposing the first and second photo resist film of step (d) to a metal etching material to etch away the metal sheet not covered by the photo resist film; and
- f. removing the photo resist film, wherein the fabric has a first and second layer of metal plates, each layer of metal plates held in a spaced array by the other layer of metal plates and the bonding spots of step (a) located so that the bonding spots connect the metal plates in the first layer of metal plates to the adjacent metal plates in the second layer of metal plates.

43. A fabric comprising connecting material, an array of metal plates affixed to the connecting material, and a mesh reinforcement of the metal plates, which plates are maintained in a spaced relationship to one another by the connecting material.
44. A fabric comprising:
 - a. a base material; and
 - b. a connecting material bonded on a surface of the base material, the connecting material having an array of metal plates affixed to the connecting material so that the connecting material maintains the plates in pre-spaced relationship to one another.
45. A fabric comprising a base material having an array of metal plates affixed to the base material so that the plates are maintained in pre-spaced relationship to one another.
46. A fabric of claim 7, wherein the layers are affixed by bonding using an array of shapes in the form of disconnected lines with neighboring disconnected lines perpendicular to each other.
47. A fabric comprising (a) a base material; (b) a connecting material supported on a first surface of the base material; and (c) a layer of plates established through the connecting material and affixed to the base material, so that the connecting material maintains the plates in a pre-spaced relationship to each other.
48. A fabric according to claim 41, wherein a first connecting material is supported on the first surface of the base material and a second connecting material is supported on a second surface of the base material;
 - a. a plate array is established through the first connecting material and affixed to the first surface of the base material and a plate array is established through the second connecting material and affixed to the second surface of the base material;

- b. so that the plates in each of the plate arrays are maintained in a pre-spaced relationship to each other; and
 - c. the first and second layers of plate arrays are oriented to each other to minimize registration of inter-plate apertures between the plate arrays in the first and second layers.
- 49. A fabric according to claim 48, wherein the plate arrays on both the first and second surfaces of the base material are selected from identical and different.
- 50. A fabric according to claim 48, wherein an array of aperture plates are affixed to the base material between the base material and at least one of the first or second layers of plate arrays in a pre-spaced relationship to each other and sized and spaced to overlap the inter-plate apertures of the first and second layers of plate arrays.
- 51. A fabric according to claim 48, wherein the plates in the first and second plate arrays are guard plates and at least one of the guard plate array layers has aperture plates affixed to the at least one guard plate array layer surface facing away from the base material, which aperture plates are maintained in a pre-spaced relationship to each other and sized and spaced to overlap the inter-plate apertures of the first and second layers of the guard plate array layers.
- 52. A fabric according to claim 47, wherein:
 - a. a first surface of a first base material is opposite a second surface of the first base material, which second surface of the first base material is covered by a first layer of plates;
 - b. a first surface of a second base material is opposite a second surface of the second base material, which second surface of the second base material is covered by a second layer of plates;

- c. the first surfaces of the first and second base material each affixed to an array of aperture plates sized and spaced to overlap the inter-plate apertures of the first and second layers of plates, so that the first and second base materials are covered by plates, selected from guard plates, aperture plates and combinations thereof; and
 - d. the first and second base materials oriented to each other to minimize registration of the inter-plate apertures between the first and second layers of plates.
- 53. A fabric according to claim 47, wherein the connecting material between the plates relieves debonding stresses on individual plates by dissipating debonding stresses throughout the plate array.
- 54. A fabric according to any of claims 47 through 53, wherein the plates are selected from penetration resistant and a heat curable epoxy.
- 55. A fabric according to any of claims 47 through 57, wherein the plates in each layer are oriented to each other so that apertures do not form a straight line across the fabric.
- 56. A fabric according to any of claims 47 through 53, wherein the connecting material is a polyester chiffon.
- 57. A fabric according to any of claims 47 through 53, wherein the base material is a non-woven polyurethane and nylon synthetic leather.
- 58. A fabric according to any of the claims 47 through 53, wherein layers, plates, or base material are affixed by bonding.
- 59. A fabric comprising:
 - a. three layers, wherein each layer is a plate array established through a connecting material, so that the connecting material

maintains the plates of the array in a pre-spaced relationship to each other;

b. the layers oriented to each other to minimize registration of the inter-plate apertures between the three layers of plate arrays; and

c. the connecting materials of adjacent layers are affixed to each other.

60. A fabric according to claim 59, wherein the adjacent layers are affixed by bonding each layer to the other at bonding spots patterned between the plates and no spots of one layer are superimposed upon spots of another layer.

61. A fabric comprising:

a. a base material; and

b. a layer supported on a first surface of the base material, the layer having a pattern of continuous and discontinuous portions with the discontinuous portions bonded through the continuous portions and into the first surface of the base material, so that the continuous portion maintains the discontinuous portions in a pre-spaced relationship to each other.

62. A fabric according to claim 61, further comprising a layer of continuous and discontinuous portions supported on a second surface of the base material with the layers oriented to each other to minimize registration of the discontinuous portions in each of the layers.

63. A fabric according to claim 62, wherein the continuous and discontinuous portions on both base material surfaces are selected from identical and different.

64. A fabric according to claim 62, wherein a layer of discontinuous portions is impressed into the base material in a pre-spaced relationship, sized, and spaced to overlap the continuous portions of the layer of continuous and discontinuous portions, so that the base material is covered by discontinuous portions of the overlapped layers.
65. A fabric according to claim 62, wherein
- a. a first layer of continuous and discontinuous portions is overlaid with a second layer of continuous and discontinuous portions, so that the first and second layers are registered to each other to minimize areas of continuous portions and so that the base material is covered by registered discontinuous portions of the layers;
 - b. and wherein the continuous portion of the second layer is bonded to the discontinuous portion of the first layer.
66. A fabric according to claim 61, wherein:
- a. a first and a second base material oriented with a second surface of the first base material opposite the second surface of the second base material;
 - b. the first and second base materials oriented to each other to minimize registration of the continuous portions which lie between the discontinuous portions in the layers on the first surfaces of the first and second base material; and
 - c. the second surface of the first base material opposite the second surface of the second base material bonded to each other by an array of discontinuous portions sized and spaced to overlap the continuous portions of the layers on the first surfaces of the first and second base materials.

67. A fabric according to any of claims 61 through 66, wherein the continuous portion between the discontinuous portions relieves debonding stresses on individual discontinuous portions by dissipating debonding stresses throughout the layer.
68. A fabric according to any one of claims 61 through 66, wherein the discontinuous portions are selected from penetration resistant and a heat curable epoxy.
69. A fabric according to any of claims 61 through 66, wherein the discontinuous portions in each layer are oriented to each other so that continuous portions do not form a straight line across the fabric.
70. A fabric according to any of claims 61 through 66, wherein the continuous portions are a polyester chiffon.
71. A fabric according to any of claims 61 through 66, wherein the base material is a non-woven polyurethane and nylon synthetic leather.
72. A fabric comprising:
 - a. three layers;
 - b. wherein each layer has a pattern of continuous and discontinuous portions, so that the continuous portion maintains the discontinuous portions in a pre-spaced relationship to each other, the layers oriented to each other to assure registration of the discontinuous portions of the three layers to each other so that the fabric is essentially completely covered by discontinuous portions; and
 - c. wherein the continuous portions of adjacent layers are bonded to each other.

73. A fabric according to claim 72, wherein the adjacent layers are bonded to each other at bonding spots patterned in the continuous portions and no spots of one layer superimpose spots of another layer.
74. A fabric according to claim 72, wherein the adjacent layers are bonded to each other at bonding spots non-commensurate with the discontinuous portions.
75. A fabric according to any one of claims 72 through 74, wherein the discontinuous portions are selected from penetration resistant and a heat curable epoxy.
76. A fabric according to any of claims 72 through 74, wherein the discontinuous portions in each array are oriented to each other so that continuous portions do not form a straight line across the fabric.
77. A fabric according to claim 72, wherein the layers are selected from identical and different.
78. A fabric according to any of claims 72 through 74, wherein the continuous portions are a polyester chiffon.
79. A fabric according to any of claims 72 through 74, wherein the base material is a non-woven polyurethane and nylon synthetic leather.
80. A method of printing polymer resin plates onto a base material comprising:
 - a. layering a connecting material onto the base material;
 - b. positioning a template atop the connecting material;
 - c. printing polymer resin plates through the connecting material into the base material;
 - d. removing the template; and
 - e. curing the polymer resin.

81. A method according to claim 80, wherein the polymer resin is a heat curable epoxy.
82. A method according to claim 80, wherein the connecting material is a polyester chiffon.
83. A method according to claim 80, wherein the base material is a non-woven polyurethane and nylon synthetic leather.




Figure 2




Figure 2




Figure 3

Figure 4A





Figure 4B






Figure 5




Figure 4




Figure 7

Figure 8A





Figure 8B






Figure 9

Figure 10A





Figure 10B






Figure //




Figure 12A




Figure 12B




Figure 13




Figure 14




Figure 15A




Figure 15B




Figure 16

Figure 17A





Figure 17B






Figure 18

Figure 19A





Figure 19B

Figure 21A





Figure 21B




Figure 22




Figure 23

Figure 24A




Figure 24B





Figure 24C






Figure 25




Figure 26A




Figure 26B






Figure 27C







FIGURE 28.








Figure 31




Figure 32




Figure 33B




Figure 34